# WORKSHOP CALCULATION & SCIENCE

# (NSQF)

## 2<sup>nd</sup> YEAR

## (As per Revised Syllabus July 2022)

## Tool & Die Maker (Dies & Moulds)



DIRECTORATE GENERAL OF TRAINING MINISTRY OF SKILL DEVELOPMENT & ENTREPRENEURSHIP GOVERNMENTOF INDIA



## NATIONAL INSTRUCTIONAL MEDIA INSTITUTE, CHENNAI

Post Box No. 3142, CTI Campus, Guindy, Chennai - 600 032

## Workshop Calculation & Science Tool & Die Maker (Dies & Moulds) - 2<sup>nd</sup> Year NSQF As per Revised Syllabus July 2022

#### **Developed & Published by**



National Instructional Media Institute Post Box No.3142 Guindy, Chennai - 600032 INDIA Email: chennai-nimi@nic.in Website: www.nimi.gov.in

Copyright © 2023 National Instructional Media Institute, Chennai

First Edition : December 2023

Copies: 1000

Rs: 125/-

All rights reserved.

No part of this publication can be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording or any information storage and retrieval system, without permission in writing from the National Instructional Media Institute, Chennai.

### FOREWORD

The Government of India has set an ambitious target of imparting skills one out of every four Indians, to help them secure jobs as part of the National Skills Development Policy. Industrial Training Institutes (ITIs) play a vital role in this process especially in terms of providing skilled manpower. Keeping this in mind, and for providing the current industry relevant skill training to Trainees, ITI syllabus has been recently updated with the help of comprising various stakeholder's viz. Industries, Entrepreneurs, Academicians and representatives from ITIs.

The National Instructional Media Institute (NIMI), Chennai, has now come up with instructional material to suit the revised curriculum for **Workshop Calculation & Science - Tool & Die Maker (Dies & Moulds) 2**<sup>nd</sup> **Year** NSQF (Revised 2022) under CTS will help the trainees to get an international equivalency standard where their skill proficiency and competency will be duly recognized across the globe and this will also increase the scope of recognition of prior learning. NSQF trainees will also get the opportunities to promote life long learning and skill development. I have no doubt that with NSQF the trainers and trainees of ITIs, and all stakeholders will derive maximum benefits from these IMPs and that NIMI's effort will go a long way in improving the quality of Vocational training in the country.

The Director General of Training, Executive Director & Staff of NIMI and members of Media Development Committee deserve appreciation for their contribution in bringing out this publication.

Jai Hind

#### ATUL KUMAR TIWARI, I.A.S.

Secretary Ministry of Skill Development & Entrepreneurship, Government of India.

December 2023 New Delhi - 110 001

### PREFACE

The National Instructional Media Institute(NIMI) was set up at Chennai, by the Directorate General of Training, Ministry of skill Development and Entrepreneurship, Government of India, with the technical assistance from the Govt of the Federal Republic of Germany with the prime objective of developing and disseminating instructional Material for various trades as per prescribed syllabus and Craftsman Training Programme(CTS) under NSQF levels.

The Instructional materials are developed and produced in the form of Instructional Media Packages (IMPs), consisting of Trade Theory, Trade Practical, Test and Assignment Book, Instructor Guide and Wall charts. The above material will enable to achieve overall improvement in the standard of training in ITIs.

A national multi-skill programme called SKILL INDIA, was launched by the Government of India, through a Gazette Notification from the Ministry of Finance (Dept of Economic Affairs), Govt of India, dated 27th December 2013, with a view to create opportunities, space and scope for the development of talents of Indian Youth, and to develop those sectors under Skill Development.

The emphasis is to skill the Youth in such a manner to enable them to get employment and also improve Entrepreneurship by providing training, support and guidance for all occupation that were of traditional types. The training programme would be in the lines of International level, so that youths of our Country can get employed within the Country or Overseas employment. The **National Skill Qualification Framework** (**NSQF**), anchored at the National Skill Development Agency(NSDA), is a Nationally Integrated Education and competency-based framework, to organize all qualifications according to a series of **levels of Knowledge**, **Skill and Aptitude.** Under NSQF the learner can acquire the Certification for Competency needed at any level through formal, non-formal or informal learning.

The **Workshop Calculation & Science -** Tool & Die Maker (Dies & Moulds) 2<sup>nd</sup> Year NSQF (Revised 2022) under CTS is one of the book developed by the core group members as per the NSQF syllabus.

The **Workshop Calculation & Science -** Tool & Die Maker (Dies & Moulds) 2<sup>nd</sup> Year NSQF (Revised 2022) under CTS as per NSQF is the outcome of the collective efforts of experts from Field Institutes of DGT, Champion ITI's for each of the Sectors, and also Media Development Committee (MDC) members and Staff of **NIMI.** NIMI wishes that the above material will fulfill to satisfy the long needs of the trainees and instructors and shall help the trainees for their Employability in Vocational Training.

NIMI would like to take this opportunity to convey sincere thanks to all the Members and Media Development Committee (MDC) members.

Chennai - 600 032

**EXECUTIVE DIRECTOR** 

## ACKNOWLEDGEMENT

The National Instructional Media Institute (NIMI) sincerely acknowledge with thanks the co-operation and contribution of the following Media Developers to bring this IMP for **Workshop Calculation & Science -Tool & Die Maker (Dies & Moulds) 2**<sup>nd</sup> **Year** as per NSQF Revised 2022.

#### MEDIA DEVELOPMENT COMMITTEE MEMBERS

Shri. M. Sangara pandian

Training Officer (Retd.) CTI, Govt. of India, Guindy, Chennai - 32.

Shri. G. Sathiamoorthy

Jr. Training Officer - SG (Retd.) Govt I.T.I, Trichy, DET - Tamilnadu.

#### **NIMI CO-ORDINATORS**

Shri. Nirmalya Nath

Deputy General Manager, NIMI, Chennai - 32.

Shri. G. Michael Johny

Manager, NIMI, Chennai - 32.

NIMI records its appreciation of the **Data Entry**, **CAD**, **DTP Operators** for their excellent and devoted services in the process of development of this IMP.

NIMI also acknowledges with thanks, the efforts rendered by all other staff who have contributed for the development of this book.

## INTRODUCTION

The material has been divided into independent learning units, each consisting of a summary of the topic and an assignment part. The summary explains in a clear and easily understandable fashion the essence of the mathematical and scientific principles. This must not be treated as a replacment for the instructor's explanatory information to be imparted to the trainees in the classroom, which certainly will be more elaborate. The book should enable the trainees in grasping the essentials from the elaboration made by the instructor and will help them to solve independently the assignments of the respective chapters. It will also help them to solve the various problems, they may come across on the shop floor while doing their practical exercises.

The assignments are presented through 'Graphics' to ensure communications amongst the trainees. It also assists the trainees to determine the right approach to solve the problems. The required relevent data to solve the problems are provided adjacent to the graphics either by means of symbols or by means of words. The description of the symbols indicated in the problems has its reference in the relevant summaries.

At the end of the exercise wherever necessary assignments, problems are included for further practice.

#### Time allotment - 2<sup>nd</sup> Year : 34 Hrs

Time allotment for each title of exercises has been given below. Workshop Calculation & Science - Tool & Die Maker (Dies & Moulds) 2<sup>nd</sup> Year NSQF Revised Syllabus 2022.

S.No	Title	Exercise No.	Time in Hrs
1	Friction	2.1.01 - 2.1.03	6
2	Centre of Gravity	2.2.04	4
3	Area of cut out regular surfaces and area of irregular surfaces	2.3.05 - 2.3.07	8
4	Elasticity	2.4.08 & 2.4.09	8
5	Heat Treatment	2.5.10 & 2.5.11	2
6	Estimation and Costing	2.6.12 - 2.6.15	6
		Total	34 Hrs

## LEARNING / ASSESSABLE OUTCOME

On completion of this book you shall be able to

- Demonstrate basic mathematical concept and principles to perform practical operations.
- Understand and explain basic science in the field of study.

### CONTENTS

Exercise No.	Title of the Exercise	Page No.
	Friction	
2.1.01	Friction - Advantages and disadvantages, Laws of friction, co-efficient of friction, angle of friction, simple problems related to friction	1
2.1.02	Friction - Lubrication	9
2.1.03	Friction - Co- efficient of friction, application and effects of friction in workshop practice	12
	Centre of Gravity	
2.2.04	Centre of gravity - Centre of gravity and its practical application	14
	Area of cut-out regular surfaces and area of irregular surfaces	
2.3.05	Area of cut-out regular surfaces - circle, segment and sector of circle	23
2.3.06	Related problems of area of cut-out regular surfaces - circle, segment and sector of circle	26
2.3.07	Area of irregular surfaces and application related to shop problems	28
	Elasticity	
2.4.08	Elasticity - Elastic, plastic materials, stress, strain and their units and young's modulus	31
2.4.09	Elasticity - Ultimate stress and working stress	43
	Heat Treatment	
2.5.10	Heat treatment - Heat treatment and advantages (Only overview required)	46
2.5.11	Heat treatment - Different heat treatment process – Hardening, tempering, annealing, normalising and case hardening (Only overview required)	48
	Estimation and Costing	
2.6.12	Estimation and Costing - Simple estimation of the requirement of material etc., as applicable to the trade - Hand injection mould assembly	57
2.6.13	Estimation and Costing - Simple estimation of the requirement of material etc., as applicable to the trade - Two cavity injection mould parts	62
2.6.14	Estimation and Costing - Problems on estimation and costing - Hand injection mould assembly	64
2.6.15	Estimation and Costing - Problems on estimation and costing - Two cavity injection mould parts	73
		, ,

## **SYLLABUS**

2<sup>nd</sup> Year

## Workshop Calculation & Science - Tool & Die Maker (Dies & Moulds) Revised syllabus July 2022 under CTS

S.no.	Syllabus	Time in Hrs
I	Friction	6
	1 Advantages and disadvantages, Laws of friction, co- efficient of friction, angle of friction, simple problems related to friction	
	2 Friction – Lubrication	
	3 Co- efficient of friction, application and effects of friction in workshop practice	
Ш	Centre of Gravity	4
	1 Centre of gravity and its practical application	
III	Area of cut-out regular surfaces and area of irregular surfaces	8
	1 Area of cut-out regular surfaces - circle, segment and sector of circle	
	2 Related problems of area of cut-out regular surfaces – circle, segment and sector of circle	
	3 Area of irregular surfaces and application related to shop problems	
IV	Elasticity	8
	1 Elastic, plastic materials, stress, strain and their units and young's modulus	
	2 Ultimate stress and working stress	
v	Heat Treatment	2
	1 Heat treatment and advantages (Only overview required)	
	2 Different heat treatment process – Hardening, Tempering, Annealing, Normalising, Case Hardening (Only overview required)	
VI	Estimation and Costing	6
	1 Simple estimation of the requirement of material etc., as applicable to the trade	
	2 Problems on estimation and costing	
	Total	34

### Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.1.01

# Friction - Advantages and disadvantages, Laws of friction, co-efficient of friction, angle of friction, simple problems related to friction

#### Introduction

When on a solid surface, another solid is rubbed a force is created between the two solids which acts in the opposite direction of motion or tries to obstruct the motion of the object, this force is called frictional force. This phenomenon is called friction. This happens due to roughness of the two surfaces.

In other words, It is the force of resistance offered to motion, experienced by bodies which are in contact. It depends upon the normal reaction between the contacting surfaces and the nature of the surfaces. No surface is absolutely friction less.

Friction plays an important role in our daily life. It would not be possible to walk without friction between our foot and floor. Vehicles are able to run on roads because of the friction between the wheels and road.



#### **Types of friction**

- 1 Static friction
- 2 Dynamic friction

#### 1 Static friction

The friction between two solid objects when at rest is called static friction.

Eg. Static friction can prevent an object from sliding down on a sloped surface.

#### **Limiting friction**

When the frictional force (F) is equal to the applied pulling force (P) then the friction between two surfaces is known as limiting friction. (i.e F=P)

#### 2 Dynamic friction

It is the friction between two objects, when are in motion is called dynamic friction. It is also called kinetic friction.

#### **Sliding friction**

It is the friction experienced by an object when its slides over another object. Sliding friction is always less than limiting friction.

#### **Rolling friction**

It is the friction that occurs when a circular object such as a ball or roller rolls on a flat surface. Rolling friction is less than sliding friction. (ball or roller bearing)

## Forces acting on a body when a pulling force is applied to move (Fig 2)

- Weight of the block acting vertically downward (W)
- The normal reaction which acts upwards (R)
- The applied pulling force (F)
- The frictional force (F<sub>f</sub>)

When the body is about to move W=R, F=P

When pulling force is increased the body starts to move.



#### Advantages of friction

- 1 Helps us to walk without slipping.
- 2 Used to stop vehicles when brakes are applied.
- 3 Movement of vehicles due to friction between revolving wheels with tyres and the road.
- 4 Power transmission using gear drive or belt pulley drive.
- 5 Using friction we can sharp any object and also to hold it.
- 6 Nails and screws are held in wood by friction.
- 7 Heat is produced when two rough surfaces are rubbed against each other.

#### **Disadvantages of friction**

- 1 It causes wear and tear of the machine parts.
- 2 It produces heat and may cause melting of machine parts. To avoid production of heat using of coolant is necessary.
- 3 It reduces efficiency of a machine.
- 4 It reduces speed of the moving object. eg. spindle, shaft, piston etc.

#### Friction can be reduced

- 1 By using suitable lubricants (oil, grease) between the moving parts.
- 2 By polishing the surface to make them smooth.
- 3 By using ball bearings and roller bearings.
- 4 By the use of wheel.

#### Laws of friction (Fig 3 & 4)

- Frictional force is directly proportional to the normal reaction between contacting surfaces.
- Frictional force acts opposite to the direction of motion.
- Frictional force depends on the nature of contacting surfaces.
- Frictional force is independent over the area and shape of contacting surfaces.





#### **Coefficient of friction**

The ratio between the limiting friction force and the normal reactions is called the co-efficient of friction.

Suppose, by applying a force P kg, the object is just fit to move, then limiting friction force will be produced in between the two surfaces. The limiting friction force will be equal to external force applied and will work in the opposite direction.

$$\therefore$$
 F = P kg

According to the second law of limiting friction force, the friction force will be proportional to normal reaction.

$$F \propto R$$
 ( $\propto$  sign is proportional to)

$$F = R x constant$$
$$\frac{F}{R} = constant$$

This constant between objects is called Co-efficient of Friction. This is represented by  $\mu$ .

$$\mu = \frac{F}{R} \text{ or } F = \mu.R$$
Co-efficient of Friction = 
$$\frac{\text{Limiting friction force}}{\text{Normal reaction}}$$

Co-efficient of friction is always constant for any two objects and it has no units.

#### Angle of friction (Fig 5)

The forces acting on a body when it is just about to move by the application of a pulling force are W, R, P and F. The forces 'R' and 'F' are compounded and we get the resultant force 'S'. The angle formed by 'S' with 'R' is the angle of friction.





#### Angle of repose (Fig 6)

A body placed on an inclined surface remains at rest till the angle of inclination equals the angle of friction. When it exceeds the body starts sliding down. This is known as angle of repose.



#### Inclined Plane (Fig 7)

According to the figure, given below plane AB is inclined  $\theta^{\circ}$  to the horizontal. On this, the vertical line working at W kg weight will make an angle with normal line of the inclined plane equal to the degree of inclination of the base at the horizontal.

The first component of weight 'W' of the object acts on the normal line and is equal to W cos  $\theta^{\circ}$ . The second component acts parallel to base and downward and is equal to sin  $\theta^{\circ}$ .



or

:.

Normal Reaction 'R' = W cos  $\theta^{\circ}$ 

Limiting Friction Force 'F' = W sin  $\theta^{\circ}$ 

$$\therefore \quad \text{Co-efficient of friction '}\mu' = \frac{F}{R}$$
$$= \frac{W \sin \theta}{W \cos \theta}$$
$$= \tan \theta$$
$$\therefore \qquad \mu = \tan \theta$$

It may also be mentioned as:

In an inclined plane, some object without any external force applied only due to W sin 0 is about to come right downwards, then the plane makes an angle equal to the angle of friction with the horizontal.

#### Force of Friction When the Force is Horizontal (Fig 8)



Let,

- P = Force required to pull the block
- F = Force of friction
- R = Normal reaction
- W = Weight of block
- $\mu$  = Co-efficient of friction between block and surface.

As per observation from the figure 8:

The block will move forward, if it has been overcome by the force of friction.

 $\therefore$  P = F (it is horizontal)

Normal reaction of block is opposite to the direction of weight.  $\therefore$  R= W

- $\therefore$  Force of friction =  $\mu$ . R
- :. Force required to move the block =  $\mu$  . R

Force of Friction When the Force is Inclined at an Angle  $\boldsymbol{\theta}$  with the Horizontal (Fig 9)

Let,

- $\theta$  = Angle of pull 'P' to move the block with the horizontal
- W = Weight of block
- R = Normal reaction

P = Pull at an angle ' $\theta$ ' with the horizontal



As per observations: from the geometry of figure 9, it is obvious:

Horizontal component of 'P' = P  $\cos \theta$ 

Vertical component of 'P' = P sin  $\theta$ 

The horizontal component P  $\cos\theta$  will be the effective pull, while the vertical component P  $\sin\theta$  will go on for reducing the normal reaction.

As per condition of equilibrium :

Algebraic sum of horizontal components = 0

$$F - P \cos \theta = 0$$

$$F = P \cos \theta$$

Algebraic sum of vertical components = 0

$$R + P \sin \theta - W = 0$$

F

We know

$$R = W - P \sin \theta$$

F = μ. R

 $P \cos \theta = \mu [W - P . \sin \theta]$ 

$$P \cos \theta = \mu \cdot W + \mu \cdot P \cdot \sin \theta = 0$$

$$P[\cos \theta + \mu . \sin \theta] = \mu . W$$

$$P = \frac{\mu \cdot W}{\cos \theta + \mu \cdot \sin \theta}$$

Force of pull required at an angle of  $\theta$  with the horizontal is given by:

$$P = \frac{\mu \cdot W}{\cos \theta + \mu \cdot \sin \theta}$$

Example

1 A force of 40 kg is required to pull a weight of 400 kg on a horizontal plane. Determine the coefficient of friction.

Coefficient of friction =  $\frac{\text{Force}}{\text{Weight}} = \frac{F}{W}$ But F = P and R = W  $\mu = \frac{F}{W} = \frac{F_f}{R} = \frac{40}{400}$  $\mu = 0.1$  2 A force for 30N is required to move a body of mass 35 kg on a flat surface horizontally at a constant velocity. Find the coefficient of friction.

Mass of the body = 
$$35 \text{ kg.} = W$$
 (By taking  
The weight force= $35 \times 10 = 350 \text{ N}$  1kg =  $10 \text{ N}$ )

$$\mu = \frac{F}{W} = \frac{F_{f}}{R} = \frac{30}{350} = \frac{3}{35} = 0.086$$
$$\mu = 0.09$$

3 A solid weights 20 kg. This is placed on a solid surface. How much force does it require to come in motion when co-efficient of friction is 0.24.

Co-efficient of friction (
$$\mu$$
) = 0.24  
Weight (W) = 20 kg  
Force required (F) = ?  
$$\mu = \frac{F}{W}$$
$$0.24 = \frac{F}{20}$$
$$F = 20 \times 0.24$$
$$F = 4.8 kg$$

4 A tanker with loaded weight of 14500 kg is running on the road. If the co-efficient friction between tyres and road surface is 0.28. Find out its force of friction.

Co-efficient of friction ( $\mu$ ) = 0.28

Force friction (F) = ?  

$$\mu = \frac{F}{W}$$

$$0.28 = \frac{F}{14500}$$

$$F = 0.28 \times 14500$$

$$F = 4060 \text{ kg.}$$

5 A force of 800 gram weight is needed to pull a block weighing 3200 gram. What is the co-efficient of friction.

Force (F) = 800 gm  
Weight (W) = 3200 gm  
Co-efficient of friction (
$$\mu$$
) = ?  
Co-efficient of friction ( $\mu$ ) =  $\frac{F}{W}$   
=  $\frac{800}{3200}$   
 $\mu$  = 0.25

6 A force of 40 kg is required to move a mass of 80 kg on a flat surface horizontally at a constant velocity. Calculate its co-efficient of friction?

Force (F) = 40 kg  
Weight (W) = 80 kg  
Co-efficient of friction (
$$\mu$$
) = ?  
Co-efficient of friction ( $\mu$ ) =  $\frac{F}{W}$   
 $\mu = \frac{40}{80}$   
 $\mu = 0.5$ 

7 A weight of 10 kg is resting on a horizontal table and can just moved by a force of 2 kg. Find the co-efficient of friction?

Weight (W) = 10 kg  
Force (F) = 2 kg  
Co-efficient of friction (
$$\mu$$
) = ?  
Co-efficient of friction ( $\mu$ ) =  $\frac{F}{W}$   
=  $\frac{2}{10}$   
 $\mu$  = 0.2

8 A body weighing 100kg is resting on a table. Find the co-efficient of friction if a force of 30 kg makes its just to move?

Weight (W) = 100 kg  
Force (F) = 30 kg  
Co-efficient of friction (
$$\mu$$
) = ?  
Co-efficient of friction ( $\mu$ ) =  $\frac{F}{W}$   
=  $\frac{30}{100}$   
 $\mu$  = 0.3

9 A metal block weighing 10 kg rests on a horizontal table. A horizontal force of 2.5 kg can just slide the block. Find the normal reaction, limiting friction and co-efficient of friction?

Weight (W) = 10 kg  
Force (F) = 2.5 kg  
R = ?  
Normal reaction = W  
Limiting friction = ?  
$$\mu$$
 = ?  
Normal reaction (R) = 10 kg

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2<sup>nd</sup> Year : Exercise 2.1.01

Limiting friction (F) = 2.5 kg

$$\mu = \frac{F}{W}$$
$$= \frac{2.5}{10}$$
$$\mu = 0.25$$

10 A wooden block weights 100 kg. If the co-efficient of friction is 0.3, find out force required to move the block.

Co-efficient of friction (
$$\mu$$
) = 0.3  
Force (F) = ?  
$$\mu = \frac{F}{W}$$
$$0.3 = \frac{F}{100}$$
$$F = 100 \times 0.3$$
$$F = 30 \text{ kg}$$

11 Calculate the angle of inclination, if a weight of 150 kg is in equilibrium, co-efficient of friction is 0.25. Calculate the force of normal reaction also.

Work done (W) = 
$$150 \text{ kg}$$

Co-efficient of friction ( $\mu$ ) = 0.25

$$\theta = ?$$
  
Force F = ?  
 $\mu = \tan \theta = 0.25$   
 $= 14^{\circ} 2' 20''$   
 $\mu = \frac{F}{W}$   
 $0.25 = \frac{F}{150}$   
F = 0.25 x 150  
F = 37.5 Kg.

12 A body of mass 60kg rests on a horizontal plane. The value of co-efficient of friction between it and the plane being 0.2. Find the work done in moving the body through a distance of 5 meters along the plane.

Co-efficient of friction ( $\mu$ ) = 0.2

Weight (W) = 60 kg Distance (S) = 5 m

Work done (W) = ?

$$\mu = \frac{F}{W}$$

$$0.2 = \frac{F}{60}$$

$$F = 60 \times 0.2$$

$$= 12 \text{ kg}$$
Work done = Force x distance = F x S
$$= 12 \times 5$$

$$= 60 \text{ Kg.m}$$

(ie) Work done (or) Applied force = 60 Kg.m

13 If a force of 30N is required to move a mass of 35kg on a flat surface horizontally at constant velocity, what will be the co-efficient of friction?

Force (F) = 30 N  
Weight (W) = 35 kg  
1 kg = 9.8 N  
35 Kg = 9.8 x 35 = 343 N  
Co-efficient of friction = 
$$\mu = \frac{F}{W}$$
  
 $= \frac{30 N}{35 \text{ kg}}$   
 $= \frac{30 N}{35 \text{ x 9.8 N}}$   
 $\mu = 0.087$ 

14 A block of ice weighing one quintal rests in equilibrium on a wooden plank inclined at 30°. Find the coefficient of friction between the ice and wood.

W = 1 quintal = 100 kg = Weight  

$$\theta$$
 = 30°  $\frac{F}{W} = \mu = \tan \theta$   
 $\mu$  = tan  $\theta$  = tan 30°  
 $\mu$  = 0.5774

15 Calculate the force that is required to slide a mass of 980 kg on a guide, when the coefficient of friction between the surfaces is 0.09.

Weight (W) = 980 kg  
Co-efficient of friction (
$$\mu$$
) = 0.09  
Force (F) = ?  
Co-efficient of friction =  $\mu = \frac{F}{W}$   
 $0.09 = \frac{F}{980 \text{ kg}}$   
F = 0.09 x 980 kg

Required force(F) = 88.2 kg

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2nd Year : Exercise 2.1.01

16 A metal block weighing 10kg rests on a horizontal board and the coefficient of friction between the surfaces is 0.22. Find (a) the horizontal force which will just move the block and (b) the force acting at an angle of 30° with the horizontal, which will just move the block.

Weight (W) = 10 kg

Co-efficient of friction ( $\mu$ ) = 0.22

(a)

(b) Force acting at an angle of 30° with the horizontal?

F = ?

 $\mu = \frac{F}{W}$ 

(a)

 $0.22 = \frac{F}{10 \text{ kg}}$  F = 2.2 Kg.(b) Force acting at an angle of 30° =  $\frac{F}{\cos \theta}$ 

= 2.2/cos 30° = 2.2/0.8660

Force acting at an angle of 30° = 2.54 kg

- 17 Calculate the angle of inclination, if a weight of 250 kg is in equilibrium. Coefficient of friction is 0.36. Calculate the force of normal reaction also.
  - Angle of inclination ( $\theta$ ) = ? Weight (W) = 250kg  $\mu$  = 0.36 Force (F) = ?

- $\tan \theta = \mu$  $\tan \theta = 0.36$  $\theta = 19^{\circ} 48'$  $\mu = \frac{F}{W}$  $0.36 = \frac{F}{250 \text{ kg}}$  $F = 0.36 \times 250 \text{ kg}$ F = 90 kg.
- 18 A body of mass 10 kg rests on a horizontal plane. The co-efficient of friction between the body and plane is 0.15. Find the work done in moving the body through a distance of 10 metre.

Co

Weight (W) = 10kg  
efficient of friction (
$$\mu$$
) = 0.15  
Distance (S) = 10 metre  
Work done (W) = ?  

$$\mu = \frac{F}{W}$$

$$0.15 = \frac{F}{10 \text{ Kg}}$$

$$F = 0.15 \text{ x 10 kg}$$

$$F = 1.5 \text{ kg}$$
Work done = W = F x S  
= 1.5 kg x 10 m  
Work done = **15 kg.m**

### Assignment A

- 1 A force 50N is required to move a mass of 40kg on a flat surface horizontally at a constant velocity. Find the coefficient of friction. (9.8N = 1kg)
- 2 A vehicle having a weight of 800kg is moving on the road. If the coefficient of friction between the tyres and road surface is 0.3, then calculate the force of friction.
- 3 A solid weighing 50kg is placed on a solid surface. How much force is required to move the block when coefficient of friction is 0.25 between the block and the surface.
- 4 A railway wagon weighs 1250 tonnes. If the coefficient of friction between it and the rails is 0.003, find the force required to move the wagon.

- 5 A body of mass 100kg rests on a horizontal plane. The angle of friction between the body and the plane being 0.025. Find the work done in moving the body through a distance of 16m along the plane.
- 6 A body of mass 20kg rests on a horizontal plane, the co-efficient of friction between the body and plane is 0.3. Find the work done in moving the body through a distance of 10 metres.
- 7 A body of mass 2000 kg moves a distance of 10 meters in 5 sec. If the co-efficient of friction between the body and floor is 0.3 find the horizontal force required to move the body and horsepower absorbed against friction.

- 8 A vehicle is moving at 50kmph and the load on the vehicle is 5000 kg. Find the H.P. required to move the vehicle if  $\mu = 0.2$ .
- 9 Find out the power lost due to friction by a planer under the following conditions.

Mass of the planer table = 3500 kg

### Assignment B

Rate of moment of the table=0.5 m/sec

Co-efficient of friction between the table and the ways=0.06

10 A truck having weight 12000 kg is moving on the road. If the co-efficient of friction between the tyres and the road surface is 0.3, then calculate the force of friction.



#### MCQ С

- 1 Which one of the following is useful friction
  - A Rings in cylinders
  - B Crankshaft bearings C Brake shoe linings D Wheel hole bearings
- 2 Which is in between the wheels and road, if vehicles are able to run on roads.
  - B motion A erosion
  - C corrosion D friction

3 Which direction of motion frictional force acts.

A	equal	В	opposite
---	-------	---	----------

- C inclined D forward
- 4 What is the formula of angle of friction, if 'F' is the frictional force, R is the normal reaction and  $\theta$  is the angle of friction.

A 
$$\operatorname{Tan} \theta = \frac{F}{R}$$
  
B  $\operatorname{Cot} \theta = \frac{F}{R}$   
C  $\operatorname{Sin} \theta = \frac{F}{R}$   
D  $\operatorname{Cos} \theta = \frac{F}{R}$ 

5 What is the formula for Co-efficient of friction (m).

A 
$$\mu = \frac{R}{F}$$
  
C  $\mu = F \times R$   
B  $\mu = \frac{F}{R}$   
D  $\mu = F + R$ 

6 A loaded truck weighs 2400 kg and it can be moved by a force of 30 kg. Determine the co-efficient of rolling friction



7 Calculate the pulling force required for the figure shown.



A	27 Kg	В	28 Kg
С	29 Kg	D	30 Kg

8 Determine the co-efficient of friction ( $\mu$ ) between brass and steel when a brass slider was placed on the horizontal steel surface until it is just moving, if brass slides (W) = 3 Kgf and required force is 0.7 Kgf.

Brass slides (W) = 3 Kgf

Force (F) required = 0.7 kgf

А	0.033	В	0.133
С	0.233	D	0.333

9 Which is necessary to avoid production of heat.

А	sand	В	coolant
С	lubricant	D	salt

- 10 Which is used to reduce the friction.
  - A lubricants B sand
  - C coal D coolant

## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.1.02 Friction - Lubrication

There are 3 systems of lubrication.

- · Gravity feed system
- Force feed system
- Splash feed system

#### **Gravity feed**

The gravity feed principle is employed in oil holes, oil cups and wick feed lubricators provided on the machines. (Figs 1 & 2)





Force feed/Pressure feed

#### Oil, grease gun and grease cups

The oil hole or grease point leading to each bearing is fitted with a nipple, and by pressing the nose of the gun against this, the lubricant is forced to the bearing. Greases are also force fed using grease cup. (Fig 3)



Oil is also pressure fed by hand pump and a charge of oil is delivered to each bearing at intervals once or twice a day by operating a lever provided with some machines. (Fig 4) This is also known as shot lubricator.



#### Oil pump method

In this method an oil pump driven by the machine delivers oil to the bearings continuously, and the oil afterwards drains from the bearings to a sump from which it is drawn by the pump again for lubrication.

#### Splash lubrication

In this method a ring oiler is attached to the shaft and it dips into the oil and a stream of lubricant continuously splashes around the parts, as the shaft rotates. The rotation of the shaft causes the ring to turn and the oil adhering to it is brought up and fed into the bearing, and the oil is then led back into the reservoir. (Fig 5) This is also known as ring oiling.



In other systems one of the rotating elements comes in contact with that of the oil level and splash the whole system with lubricating oil while working. (Fig 6) Such systems can be found in the headstock of a lathe machine and oil engine cylinder.



#### Types of grease guns

The following types of grease guns are used for lubricating machines.

• 'T' handle pressure gun (Fig 7)



Automatic and hydraulic type pressure gun (Fig 8)



• Lever-type pressure gun (Fig 9)



Lubrication to exposed slideways

The moving parts experience some kind of resistance even when the surface of the parts seems to be very smooth.

The resistance is caused by irregularities which cannot be detected by the naked eyes.

Without a lubricant the irregularities grip each other as shown in the diagram. (Fig 10)



With a lubricant the gap between the irregularities fills up and a film of lubricant is formed in between the mating components which eases the movement. (Fig 11)

The slideways are lubricated frequently by an oilcan. (Fig 12)  $\,$ 



After cleaning the open gears, oil them and repeat lubrication regularly. (Fig 13)



#### Lubricate bearings

A shaft moving in a bearing is also subjected to frictional resistance. The shaft rotates in a bush bearing or in ball/ roller bearing, experiencing friction.

When the shaft is at rest on the bottom of the bush bearing, there is hardly any lubricant between the shaft and the bush. (Fig 14)



When the shaft starts rotating the lubricant maintains a film between the shaft and the bush and an uneven ring of lubricant builds up. (Fig 15)



When the shaft is rotating at full speed a full ring of lubricating film surrounds the shaft (Fig 16) which is known as hydro dynamic lubrication.



This lubrication ring decreases the frictional resistance very much and at the same time protects the mating members against wear and changes.

Some bush bearings have oil feeding holes over which the oil or grease cup is mounted and the lubricant is fed through the holes into the bearing by gravity feed system. (Fig 17)



#### Hints for lubricating machines:

- identify the oiling and greasing points
- select the right lubricants and lubricating devices
- apply the lubricants.

The manufacturer's manual contains all the necessary details for lubrication of parts in machine tools. Lubricants are to be applied daily, weekly, monthly or at regular intervals at different points or parts as stipulated in the manufacturer's manual.

These places are indicated in the maintenance manuals with symbols as shown in Fig 18.



## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.1.03 Friction - Co -efficient of friction, application and effects of friction in workshop practice

i)

ii)

i)

ii)

#### **Co-efficient of friction**

The ratio between the limiting frictional force and the normal reaction is called co-efficient of friction.

Suppose, by applying a force 'P' kg, the object is just fit to move, then limiting frictional force will be produced in between the two surfaces. The limiting frictional force will be equal to external force applied and will work in the opposite direction.

∴ F = P kg

According to the second law of limiting frictional force, the frictional force will be proportional to normal reaction.

$$F \propto R \pmod{sign is proportional to}$$

F = R x constant

or 
$$\frac{F}{R}$$
 = constant

This constant between objects is called co-efficient of friction. This is represented by  $\mu$ .

$$\mu = \frac{F}{R} \text{ or } F = \mu.R$$

Co-efficient of friction =  $\frac{\text{Limiting frictional force}}{\text{Normal reaction}}$ 

Co-efficient of friction is always constant for any two objects and it has no unit.

#### Example

1 The sliding valve of a steam engine has dimensions 25cm by 45 cm and the steam pressure on the back of the valve is 25 kg/cm<sup>2</sup>. If the co-efficient of friction is 0.13. Calculate the force required to move the valve?

Dimension of steam value = 25 cm x 45 cm.

Steam pressure = 25 kg/cm<sup>2</sup>

Co-efficient of friction = 0.13

Force required to move the valve = ?

Force of the steam = Pressure x Area =  $25 \times 25 \times 45$ 

 $\frac{25\text{kg}}{\text{cm}^2}$  × 25 cm × 45 cm = 28125 kg.

Force acts on the valve = 28125 kg

$$\mu = \frac{F}{W}$$
$$0.13 = \frac{F}{28125}$$
$$F = 0.13 \times 2812$$

Force required to move the valves = 3656.25 Kg

2 An empty drum weighing 50kg is resting on a shop floor. Find the coefficient of friction if a force of 15kg makes it just move.

Weight (W) = 50 kg  
Force (F) = 15  
Co-efficient of friction 
$$\mu = \frac{F}{W}$$
  
 $= \frac{15 \text{ kg}}{50 \text{ kg}}$   
 $\mu = 0.3$ 

3 A machine crate weighing 1000kg moves distance of 5m in 5 sec. If the coefficient of friction between the crate and floor is 0.3, calculate the horizontal force required to move the crate and horse power absorbed against friction.

Weight (W) = 1000 kg  
Distance (S) = 5 meter  
Time (t) = 5 second  
Co-efficient of friction (
$$\mu$$
) = 0.3  
Force (F) = ?  
Horse power (H.P.) = ?  

$$\mu = \frac{F}{W}$$

$$0.3 = \frac{F}{1000 \text{ Kg}}$$

$$F = 0.3 \times 1000 \text{ kg}$$

$$F = 300 \text{ kg}$$

$$(1 \text{ HP} = 75 \text{ m.kg/sec})$$

$$H.P = \frac{F \times S}{t} \times \frac{1}{75}$$

$$H.P = \frac{300 \times 5}{5} \times \frac{1}{75} = 4 H.P$$

Horse power absorbed against friction = 4.H.P.

4 A weight of 600 kg is kept on the inclined plane at 30°. Calculated the normal reaction and force rolling downwards.

Solution:

Weight kept on the inclined plane (W) = 600kg

Angle of the inclined plane ( $\theta$ ) = 30<sup>o</sup>

 $\therefore$  Normal reaction (R) = W  $. \cos \theta$ 

= 600 x cos 30°
 = 600 (0.8660)
 = 519.6 kg
 Force rolling downwards
 = W . sin θ
 = 600 x sin 30°
 = 600 (0.5000)
 = 300 kg
 ∴ Normal reaction
 = 519.6 kg
 Force rolling downwards
 = 300 kg

5 Find out the power lost due to friction by a planner under the following conditions.

Mass of the planer ta	able	= 3500 kg					
Rate of movement o	= 0.5m/sec						
Co-efficient of friction between = 0.06							
Solution:							
Weight of planer (W) = 3500 kg							
Distance moved (d)	= 0.5 m/se	ec					

Co-efficient of friction ( $\mu$ ) = 0.06

Co-efficient of friction

$$\mu = \frac{F}{W}$$

0.06  $= \frac{F}{3500}$ F  $= 0.06 \times 3500 = 210 \text{ kg}$ Workdone  $= F \times \text{distance moved}$   $= 210 \times 0.5 = 105 \text{ kgm/sec}$ 75 kgm/sec = 1 H.P  $105 \times 1$ 

105 kgm/sec = 
$$\frac{105 \times 1}{75}$$
 = 1.4 H.P

Power lost due to friction = 1.4 H.P

- 6 A planner table weighing 800 kg moves a distance of 2 metres in seconds on its bed. If co-efficient of friction between bed and table is 0.30 find the power required to move the table against the friction.
- 7 On a milling machine table a component of 20 kgf is clamped with the help of three equidistant clamps. What force must be exerted by each clamp to avoid slipping of the component when the horizontal cutting force is 60 kgf and the coefficient of friction is equal to 0.2.
- 8 A machine weight of 14500 kg moving on the floor. If the co-efficient of friction between the machine and floor surface is 0.28 then calculate the force of friction.
- 9 A tail stock of a lathe has a mass of 21.5 kg and co-efficient of friction at the slides is 0.122. What horizontal force will be required to slide the tail stock?
- 10 An inclined surface makes an angle of 30 degrees with the horizontal. An object weighting 5 tons is placed on the surface. Find out the normal reaction at the object and also the effective force required to bring the object downwards.

## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.2.04 Centre of gravity - Centre of gravity and its practical application

Any object comprises of a large number of particles. Each particle is pulled towards the earth due to the force of gravity. Thus, the forces on the particles are equal, parallel and act in the same direction. These forces will have a resultant which acts through a particular point 'G'. This fixed point 'G' is called the centre of gravity. (Fig 1)





In physics, an imaginary point in a body of matter where, for convenience in certain calculations, the total weight of the body may be thought to be concentrated. The concept is sometimes useful in designing static structures (e.g., buildings and bridges) or in predicting the behaviour of a moving body when it is acted on by gravity.

In a uniform gravitational field the centre of gravity is identical to the centre of mass, a term preferred by physicists.



#### Gravitation

The mutual attractive force of bodies due to which they attract each other is called gravitation.

#### 1 Gravity

The attractive force of the earth due to which it attracts all bodies towards its centre is called gravity.

The value of gravity varies from place to place on the ground surface. Its general value is  $9.81 \text{ m/s}^2$ .

#### Centroid

Different geometrical shapes such as the circle, triangle and rectangle are plane figures having only 2-dimensions. They are also known as laminas. They have only area, but no mass. The centre of gravity of these plane figures is called as the Centroid. It is also known as the geometrical centre. The method of finding out the centroid of a plane figure is the same as that of finding out the centre of gravity of a body. If the lamina is assumed to have uniform mass per unit area, then the centroid is also the centre of gravity in a uniform gravitational field.

#### Methods to calculate centre of gravity

- 1 By geometrical consideration.
- 2 By moments.

**Principle :** The total moment of a weight about any axis = The sum of the moments of the various parts about the same axis.

3 By graphical method.

The first two methods are generally used to find out the centre of gravity or centroid, as the third method can become tedious.

#### Centre of gravity by geometrical consideration (Fig 3)



- 1 The centre of gravity of a circle is its centre.
- 2 The centre of gravity of a square, rectangle or a parallelogram is at the points where its diagonals meet each other. It is also the middle point of the length as well as the width.
- 3 The centre of gravity of a triangle is at the point where the medians of the triangle meet.
- 4 The centre of gravity of a right circular Cone is at a  $\frac{1}{4}$  h distance of from its base.

5 The centre of gravity of a hemisphere is at a distance  $\frac{3r}{8}$  of from its base.

- 6 The centre of gravity of a semicircle is at a perpendicular distance of  $\frac{4r}{3\pi}$  from its centre.
- 7 The centre of gravity of a trapezium with parallel side

'a' and 'b' is at a distance of  $\frac{h}{3}\left(\frac{a+2b}{a+b}\right)$  measured from the base 'a'.

- 8 The centre of gravity of a cube of side 'L' is at equal distance from every face.
- 9 The centre of gravity of a Sphere of diameter 'd' is at a

distance of  $\frac{1}{2}$ d from every point (or) sphere centre.

#### Centre of gravity; An experiment

- Number of pencil = 2
- A fine edge like a ruler or a credit card
- A permanent marker
- A ruler

#### Step 1

Attempt to balance the pencil on the edge you have selected

Balancing the pencil may take some trial and error. The point at which the pencil balances may not be where you first thought. If it begins to tip in one direction, move the pencil back slowly in the opposite direction until it will stay there on its own.

#### Step 2

Once the pencil is balanced, mark the location of the balancing point with a permanent marker.

#### Step 3

Measure the distance between the ends of the pencil and the balancing point you have marked. Are the two lengths equal? On my pencil, the length from the eraser to the balancing point was actually 1.25 inches less than the length from the pencil tip to the balancing point. Why would this be the case?

In our experiment, the balancing point was another word for the centre of gravity of this pencil. In other words, if we cut the pencil in two at the mark we made in the experiment, the two parts would be equal in weight. However, they are not equal in length. As you may have already figured out, the metal piece that houses the eraser contributes more to the weight of the pencil, so the CG is closer to that side of the pencil.

#### Keeping up with that centre (Fig 4)

The centre of gravity is an important concept in determining the stability of a structure. It's the reason why a good homeowner will keep the top branches of his trees trimmed. It's also the reason why a pick-up truck might not be the best vehicle choice for a first time driver. Stability is maximized in objects with a lower centre of gravity and a wide base. The taller and more top-heavy an object, the more likely it is to tip over when it is tilted by a force. This figure demonstrates a bus driving on two different grades; the second one is steep enough to cause the centre of gravity to fall outside of the base of the vehicle, which will cause it to topple over.



#### Equilibrium

A body is said to be in equilibrium if the resultant of all the forces acting on a body is zero and if there is no turning moment.

There are three states of equilibrium (Fig 5)

- Stable equilibrium 1
- Unstable equilibrium 2
- 3 Neutral equilibrium



#### 1 Stable equilibrium

A body is said to be in a stable equilibrium if it returns to its original position when slightly displaced. (The C.G. is as low as possible).

- E.g : 1 A cone resting on its base (Fig 6)
  - 2 A ball on a concave surface
  - 3 Funnel resting on its base.



#### 2 Unstable equilibrium

A body is said to be in an unstable equilibrium if it does not return to its original position when slightly displaced. Its centre of gravity falls taking it away from its original position. (CG is at high points)

#### E.g: 1 A cone resting on its tip (Fig 7)

- 2 A ball on convex surface
- 3 Funnel standing on its tube end.



#### 3 Neutral equilibrium

A body is said to be in a neutral equilibrium if on being slightly displaced, it takes a new position similar to its original one. The centre of gravity remains undisturbed. (CG is neither raised or lowered)

- Eg: 1 A cone resting on its side (Fig 8)
  - 2 A ball on flat surface
  - 3 Funnel resting on its side



#### Model 1

Conditions for stable equilibrium

- The CG should be as low as possible.
- It should have a broad base.
- The vertical line passing through the CG should fall within the base.

#### Conditions of equilibrium

A body is said to be in a state of equilibrium under the action of forces when there is no motion of rotation or translation of the body. There are three conditions of equilibrium of a body which are given below:

i Algebraic sum of the horizontal components of all the forces acting on the body must be zero.

 $\Sigma H = 0$ 

ii Algebraic sum of the vertical components of all the forces acting on the body must be zero.

 $\Sigma V = 0$ 

iii Algebraic sum of the moments of all the forces acting on the body must be zero.

 $\Sigma M = 0$ 

Torque or twisting moment of a couple is given by the product of force applied and the arm of the couple (i.e. Radius). In fact, moment means the product of "force applied" and the "perpendicular distance of the point and the line of the force".

#### Some example of equilibrium in daily life

- 1 The lower decks of the ships are loaded with heavy cargoes. This makes the centre of gravity of the whole ship lower and its equilibrium becomes more stable.
- 2 A man carrying a bucket full of water in one hand extends his opposite arm and bends his body towards it.
- 3 While carrying load on back the man bends forward so that his and the load's centre of gravity falls on his feet, if he walks erect, he will fall backward.
- 4 While climbing a mountain, a man bends forward and bends backward while descending so that the centre of gravity of his load falls on his feet.
- 5 In a double-decker, more passengers are accommodated in the lower deck and less on the upper so that the centre of gravity of the bus and the passengers is kept low to eliminate any chance of tilting.

#### Example

1 Find the centroid of the isosceles triangular plate as shown in the figure.



Since  $\angle BCD=45^{\circ}$  then BD=DC = x

As per Pythagoras theorem

$$BD^{2} + DC^{2} = CB^{2}$$

$$x^{2} + x^{2} = 40^{2}$$

$$2x^{2} = 1600$$

$$x^{2} = \frac{1600}{2} = 800$$

$$x = \sqrt{800} = 28.28 \text{ cm}$$

Centroid from DB =  $\frac{x}{3} = \frac{28.28}{3} = 9.43 \text{ cm}$ 

2 A rectangular lamina has 10 cm and 8 cm. Find the centroid. (Centroid of rectangular = Diagonals intersecting point.)

Centroid of rectangular = Diagonals intersecting point

Centre of AB = 
$$\frac{10}{2}$$
 = 5  
Centre of AD =  $\frac{8}{2}$  = 4

Centroid lying 4 cm from AB and 5 cm from AD



3 A thin lamina is shown in the figure below. Find the centre of gravity.



Centroid of rectangle

Area of rectangle= 5 x 10 = 50 cm<sup>2</sup>  
Area of triangle = 
$$\frac{1}{2}$$
 bh  
=  $\frac{1}{2}$  x 5 x 5 = 12.5 cm<sup>2</sup>  
Total area = 50 + 12.5 = 62.5 cm<sup>2</sup>

The centre of gravity for rectangle is the point of intersection of diagonal = 5 cm distance from AD (CG<sub>1</sub>)

Centre of gravity for triangle is  $\frac{1}{3}$  distance from its height.

$$= 5 \times \frac{1}{3} = \frac{5}{3} = 1.67 \text{ cm}$$

 $(CG_2)$  Centroid of plate is lying in between  $CG_1$  and  $CG_2$ . From the figure torque is about AD.

$$62.5x = 50 \times 5 + 12.5 \times 11.67$$
$$= 250 + 145.875$$
$$62.5x = 395.875$$
$$x = \frac{395.875}{62.5} = 6.334 \text{ cm}$$

Centre of gravity is 6.334 cm from AD, on the centre axis.

4 A thin lamina consists of an isosceles triangle of height 120mm and base 100mm placed on a semicircle of diameter 100mm. find the location of its centre of gravity.



Area of right angled triangle (a<sub>1</sub>) = 
$$\frac{1}{2}$$
 bh  
=  $\frac{1}{2}$  x 10 x 12  
= 60 cm<sup>2</sup>

Centroid of right angled triangle = 
$$\frac{1}{3}$$
 h from base

$$=\frac{1}{3} \times 12$$

Centroid from E = 4 cm Centroid from A (h<sub>1</sub>) = 12 - 4 = 8 cm Area of half circle (a<sub>2</sub>) =  $\frac{1}{2} \pi r^2$ = $\frac{1}{2} \times 3.14 \times 5 \times 5$ 

Centroid of semi circle = (Vertical distance from centre of diagonal)

$$= \frac{4r}{3\pi}$$
  
Centroid distance from E to D 
$$= \frac{4 \times 5}{3 \times 3.14}$$
$$= 2.123 \text{ cm}$$

$$(h_2) = \begin{pmatrix} \text{Height of} \\ \text{triangle} \end{pmatrix} + \begin{pmatrix} \text{Centroid of} \\ \text{half circle} \end{pmatrix}$$
  
= 12 + 2.123  
= 14.123 cm

To find centroid of lamina

$$y = \frac{a_{1}h_{1} + a_{2}h_{2}}{a_{1} + a_{2}}$$

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2<sup>nd</sup> Year : Exercise 2.2.04

$$= \frac{60 \times 8 + 39.25 \times 14.123}{60 + 39.25}$$

$$480 + 554 \cdot 328$$

99.25

 $=\frac{1034.328}{99.25}$ 

#### Centroid is lying at 10.421 cm from point A

5 A uniform rod weighing 50kg and 3m long carries loads as shown below. Find out the distance of the CG of the system from the left hand end.



Distance of CG from A = x

 $110 x = (50 \times 1.5) + (15 \times 1.75) + (20 \times 2.25) + (25 \times 2.75)$ 

= 75 + 26.25 + 45 + 68.75 = 215

Therefore  $x = \frac{215}{110} = 1.96 \text{ m}$ 

Distance of CG of the system from A = 1.95 m

6 A long shaft is composed of two section A and B each 3 meter long and weight 36KN and 20KN respectively. Find out the position of centre of gravity of the shaft.



#### Solution

Let G<sub>1</sub> be the c.g. point of section A

Let  $G_2$  be the common c.g. of the shaft and its distance is D from left hand end.

Now, take moments about 'O'

A Moment of section A about O = 36 KN x 1.5 m

Moment of section B about O = 20 KN x 4.5 m

Adding both we get as below

Total moment about O=(36 KN x 1.5 m + (20KN x 4.5m)

= 54 KNm + 90KNm

= 144 KNm

**B** This moment is equal to moment of section A and section B about 'O' (distance of action being D metre)

That is =(36KN+20KN) x D(meter)=56 DKNm

$$\frac{44 \text{ KNm}}{56 \text{ KNm}} = D$$
$$\frac{144}{56} = D$$

Therefore D = 
$$\frac{18}{7}$$
  
= 2.57 meters

The distance of CG of the shaft from left hand is 2.57 metres.

7 A thin lamina is shown in the figure. Find centre of gravity.



As the body is symmetrical about y-axis centre of gravity lies on this axis.

Let AB is the axis of reference

Let y = The distance between centre of gravity and point F, the point of reference as shown in the figure.

Let a<sub>1</sub> = Area of rectangle CDBA = 45 x 40 = 1800 mm<sup>2</sup>

 $h_1$  = Distance between centre of gravity of rectangle of

point F = 
$$\frac{40}{2}$$
 = 20 mm

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2<sup>nd</sup> Year : Exercise 2.2.04

Let  $a_2$  = Area of triangle ECD=1/2 x base x height

=1/2 x 45 x 50 = 1125 square mm

 $h_2$  = distance between centre of gravity of triangle of point F.

=1/3<sup>rd</sup> height of triangle +width of rectangle

$$=\frac{1}{3}(50) + 40 = \frac{50}{3} + 40 = \frac{170}{3}$$
 mm

Applying formula

$$y = \frac{a_1n_1 + a_2n_2}{a_1 + a_2}$$
$$= \frac{1800(20) + 1125\left(\frac{170}{3}\right)}{1800 + 1125}$$
$$= \frac{36000 + 63753.75}{2925} = \frac{99753.75}{2925}$$

y = 34.10 mm

The CG is at a distance of 34.1mm from point F the point of reference in the line AB.

#### 8 Find the CG of the lamina shown below.



CG is in PQ

 $CG_1, CG_2 \text{ and } CG_3 \text{ - centres of centre of gravity.}$ Area of  $A_1 = 60 \times 20 \text{ mm}^2$ 



Distance of CG<sub>2</sub> from AB =  $20 + \frac{30}{2}$  mm

= 20 + 15 mm

= 35 mm

 $\Delta\,$  PTR - Isosceles triangle

Draw perpendicular line PS on TR from P.

 $\Delta$  PSR - right angled triangle

By applying Pythagoras theorem,

$$x^{2} + x^{2} = 40^{2}$$

$$2x^{2} = 1600$$

$$x^{2} = 800$$

$$x = \sqrt{800}$$

$$= 28.28 \text{ mm}$$
Area of triangle =  $\frac{1}{2} \times b \times h \text{ mm}^{2}$ 

$$= \frac{1}{2} \times 56.56 \times 28.28 \text{ mm}^{2}$$

$$= 800 \text{ mm}^{2}$$

Distance of CG<sub>3</sub> from TR =  $\frac{x}{3} = \frac{28.28}{3}$  mm = 9.43 mm

Dist. Of  $CG_3$  from AB = 20 + 30 + 9.43 mm = 59.43 mm

Total area =1200 + 450 + 800 mm<sup>2</sup> = 2450 mm<sup>2</sup>

Distance from AB = Ymm

Taking moment at AB 2450 y = 1200 x 10 + 450 x 35 + 800 x 59.43

= 75294

$$y = \frac{75294}{2450} = 30.73 \text{ mm}$$

Distance of CG is on the line PQ from side AB = 30.73 mm.

9 A steel square rod 100x12x12cm has a hole dia 6cm drilled in it as shown in the figure. Find the position of the C.G. of the square rod.



WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2nd Year : Exercise 2.2.04

	Volume of circle	= $\pi r^2 h$ unit <sup>3</sup>
		$= \pi \times 3 \times 3 \times 12 \text{ cm}^3$
		= 339.3 cm <sup>3</sup>
	Remaining volume	= 14400 - 339.8 cm <sup>3</sup>
		= 14060.7 cm <sup>3</sup>
C.	G is on PQ	
	CG in before drilling	= C.G <sub>1</sub>
	CG in before drilling	= C.G <sub>2</sub>
	CG in after drilling	= C.G
	Calculating the mom	ent on side AB
	Distance of CG <sub>1</sub>	$=\frac{100}{2}=50$ cm
	Distance of $CG_2$	= 10 cm
	Distance of C.G	= <i>x</i>
	14060.7 x <i>x</i> + 339.3	x 10 =14400 x 50
	14060.7 <i>x</i> + 3393	= 720000
	14060.7 <i>x</i>	= 720000 - 3393
		= 716607
	x	= $\frac{716607}{14060.7}$ = 50.97 cm

C.G. of the square rod = 50.97 cm from side AB.

#### 10 Centre of gravity in a lamina (Area)

Find the position of c.g of the area shown in Fig10. (All dimensions are in mm.)



#### Solution

Taking moments of area about the line **ab**, we get the equation as below.

Moment of area **abcd**+moment of area **efgh**=moment of area of complete figure.

Now to calculate the areas

1 Area of **abcd** = 120 mm x 50 mm

= 6000 mm<sup>2</sup>

Area of **efgh =** 200 x 75 mm<sup>2</sup>

= 15000 mm<sup>2</sup>

Total area = (6000+15000) mm<sup>2</sup>

 $(abcd+efgh) = 21000 \text{ mm}^2$ 

2 (6000  $m^2 x 25$ ) + (15000  $mm^2 x 150 mm$ )

 $= (21000 \text{ mm}^2) \text{ x} (x \text{ mm})$ 

150000mm<sup>2</sup> + 2250000mm<sup>2</sup> = (21000 mm<sup>2</sup>) x (x mm)

 $240000 \text{ mm}^2 = (21000 \text{ mm}^2) \text{ x} (x \text{ mm})$ 

Therefore 
$$x = \frac{2400000 \text{ mm}^2}{21000 \text{ mm}^2}$$
  
=  $\frac{2400}{21} \text{ mm}$   
=  $\frac{800}{7} \text{ mm}$   
= 114.3 mm

Hence c.g. point of composite figure is 114.3 mm from the line ab.

11 Centre of gravity point of a composite body can be found out by using a variation of principle of moments.

Example (Fig 11)



Moment of part "A" about O+ Moment of part "B" about O=Moment of (A+B) about O.

## The moment of the (A+B) acting through point G.

A copper cube of 100mm side is attached to brass cube of 100 mm side as sketched in the figure (Fig 12) Calculate the position of c.g of composite object. Take densities of copper and brass as  $8.9 \text{ gms/cm}^3$  and  $8.5 \text{ gms/cm}^3$ .

#### Solution

Volume of Copper/Brass cube = 100 x 100 x 100 mm<sup>3</sup>

= 10<sup>6</sup> mm<sup>3</sup>

$$= \frac{10^{6} \text{ mm}^{3}}{10^{3} \text{ mm}^{3}}$$

$$= 1000 \text{ cm}^{3}$$
Mass of copper cube = Volume x Density  

$$= 1000 \text{ x } 8.9$$

$$= 8900 \text{ gms}$$

$$= \frac{8900}{1000} \text{ Kg}$$

$$= 8.9 \text{ Kg.}$$
(g=Acceleration due to gravity=10m/sec<sup>2</sup>)  
Weight of copper cube = 8.9 kg x 10 m/sec<sup>2</sup>  
Similarly = 89 N  
Weight of brass cube =  $\frac{1000 \text{ cm}^{3} \text{ x } 8.5 \text{ x } 10}{1000}$ 
(Take g = 10m/sec<sup>2</sup>) = 8.500 x 10 = 85N  
Let cg of separate cubes be G<sub>c</sub> and G<sub>B</sub> as shown  
in figure.

The distance between  $\rm G_{c}$  and  $\rm G_{B}=100mm$  or 0.1 m

Let c.g of the total object be at G which is 'P' metre to the right of  $G_c$  or (0.1-P) metre to the left of  $G_B$ .

Take moments about G

Clock moments = 
$$W_B \times (0.1 - P)$$
  
=  $85 \times (0.1 - P)$ )  
=  $8.5 - 85P$   
Anti clock moments =  $W_C \times P$   
=  $89 \times P[Nm]$   
=  $89P$ 

By principle of moments

89P = 8.5 - 85P [Equating clock moments with anti-clock moments]

 $P = \frac{8.5}{174}$  metre or 0.049 m or 49 mm

Centre of gravity of the composite object lies 49 mm from point of  $G_{\rm c}$ . Hence it lies within copper cube.

### **Assignment A**

1 Find the position of centre of gravity of the figure shown. (All dimensions in mm)



2 A lamina consists of a square of 60mm side, on one side of which an equilateral triangle is constructed. Find the position of centroid of the composite.



3 A steel strip 50x12x12cm has a hole of 8cm dia. drilled through it at a distance of 10cm from end. Find out the c.g of the strip.



4 Find out the C.G. of the four sided figure ABCD when  $\angle A = \angle B = 90^{\circ}$  and the side AB=15cm, BC=12cm and AD=5cm.



WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2<sup>nd</sup> Year : Exercise 2.2.04

### Assignment B

1 What is the centre of gravity of a semi-circle is at a perpendicular distance from its centre?

A 
$$\frac{3r}{4\pi}$$
 B  $\frac{4r}{3\pi}$   
C  $\frac{8r}{3}$  D  $\frac{3r}{8}$ 

2 What is the centre of gravity of a hemisphere is at a distance from its base.

A	<u>2r</u> 8	В	<u>3r</u> 8
С	<u>4r</u> 8	D	<u>5r</u> 8

3 What is the centre of gravity of a triangle is at the point where the medians of the triangle meet?

A	<u>h</u> 2	В	<u>h</u> 3
С	<u>h</u> 4	D	<u>h</u> 5

4 What is the centre of gravity of a right circular cone is at a distance from its base.



A more weight is concentrated B less weight is concentrated C less mass is concentrated D more mass is concentrated 6 Centre of gravity of an object depends on it's. A weight B mass C density D shape 7 Point where whole weight of body acts vertically is called. A centre of mass B mid point C centre of gravity D none of above 8 A simple method to find centre of gravity of a body is usage of. A stop watch B plumbline C pendulum D screw gauge If a material has no uniform density throughout the body, 9 then the position of centroid and centre of mass are. A identical B not identical C independent upon the density D unpredictable 10 Which of the following laminas do not have centroid at its geometrical centre?

5 Centre of gravity is usually located where.

- A Circle B Equilateral triangle
- C Right angled triangle D Isosceles triangle

## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.3.05 Area of cut-out regular surfaces - Circle, segment and sector of circle

#### Circle (Fig 1)

It is the path of a point which is always equal from its centre is called a circle.

r = radius of the circle

Area of the circle =  $\pi r^2$ 

$$(or) = \frac{\pi}{4} d^2 unit^2$$

#### Circumference of the circle = $2\pi r$ (or) $\pi d$ unit



#### Sector of a circle (Fig 2)

The area bounded by an arc and two side radius is called the sector of a circle. In the figure given ABC is the sector of a circle.

r = radius of the circle

$$\theta$$
 = Angle of sector in degrees

Area of sector ABC

$$=\frac{\pi r^2 x \theta}{360^{\circ}} \text{ unit}^2$$

Area of sector =

Length of arc of sector × radius unit<sup>2</sup>

Length of the arc  $\ell = 2\pi r \times \frac{\theta}{360^{\circ}}$  unit

Perimeter of the sector =  $\ell$  + 2r unit

r = radius



#### Segment of a circle (Fig 3)

When a circle is divided into two by drawing a line, the bigger part is called segment of the circle and the smaller part is also called segment of the circle.



Area of the smaller segment

= Area of the sector - Area of  $\triangle$  ABC

Area of the greater segment

= Area of the circle - Area of smaller segment

#### Semi Circle (Fig 4)

• A semi circle is a sector whose central angle is 180°.



Length of arc of semi circle

$$\ell = 2\pi r \times \frac{180^{\circ}}{360^{\circ}} = 2\pi r \times \frac{1}{2} \text{ unit}$$
$$= \pi r \text{ unit}$$

Area of semi circle = 
$$\frac{\pi r^2}{2}$$
 unit<sup>2</sup>

Perimeter of a semi circle =  $\frac{2\pi r}{2} + 2r$ 

 $= \pi r + 2r$ 

$$= r (\pi + 2)$$
 unit

#### Quadrant of a circle (Fig 5)

• A quadrant of a circle is a sector whose central angle is 90°.



• Length of arc of quadrant of a circle

$$\ell = 2\pi r \times \frac{90^{\circ}}{360^{\circ}}$$
$$= 2\pi r \times \frac{1}{4}$$
$$= \frac{\pi r}{2}$$

Area of quadrant of a circle = 
$$\frac{\pi r^2}{4}$$
 unit<sup>2</sup>

Perimeter of a quadrant =  $\frac{2\pi r}{4} + 2r$ 

$$=\frac{\pi r}{2} + 2r$$
$$= r\left(\frac{\pi}{2} + 2\right)$$
 unit

#### Examples :

1 Find the area of a sector of a circle whose radius is 14 cm and the length of the arc of the sector is 28 cm.

Radius of sector r = 14 cm

Length of arc of sector = 28 cm

Length of arc of sector 
$$(\ell) = \frac{\theta}{360^{\circ}} \times 2\pi r$$
 unit

28 = 
$$\frac{\theta}{360^{\circ}} \times 2 \times \frac{22}{7} \times 14$$
 unit

$$\theta = \frac{28 \times 360^{\circ} \times 7}{2 \times 22 \times 14} = 114.55$$

θ

:. Angle of sector  $\theta = 114.55^{\circ}$ 

: Area of sector

Area of sector

$$= \frac{114.55}{360^{\circ}} \times \pi r^{2} \text{ unit}^{2}$$
$$= \frac{114.55}{360^{\circ}} \times \frac{22}{7} \times 14 \times 14 \text{ cm}^{2}$$
$$= 196 \text{ cm}^{2}$$
$$= 196 \text{ cm}^{2}$$

2 If the circumference of a circle is 44 cm, find its

area. (Take 
$$\pi = \frac{22}{7}$$
)

#### Solution

- : Let (d) = diameter of circle
- $\therefore$  Circumference of circle =  $\pi d$

 $\therefore 44 = \pi . d$ 

$$d = \frac{44}{\pi} = 44 \div \pi$$
$$= 44 \div \frac{22}{7}$$
$$= 44 \times \frac{7}{22}$$

: Diameter of circle (d) = 14 cm

: Area of circle 
$$=\frac{\pi}{4}d^2$$
 unit<sup>2</sup>

$$=\pi \times \frac{1}{4}d^{2}$$
$$=\frac{22}{7} \times \frac{1}{4} \times 14 \times 14$$
$$= 154 \text{ cm}^{2}$$

Area of circle = 154 cm<sup>2</sup>

3 Find the remaining area of circle of 10 cm dia after inscribing triangle of 5 cm base and 10 cm height.

#### Solution

(i) Area of the circle 
$$= \frac{\pi}{4} d^{2}$$
$$= \frac{22 \times 10 \times 10}{7 \times 4} \text{ Unit}^{2}$$
$$= \frac{550}{7} = 78.57 \text{ cm}^{2}$$
(ii) Area of the triangle inequired in this circle

(ii) Area of the triangle inscribed in this circle

$$=\frac{1}{2} \times base \times height$$
$$=\frac{10 \times 5}{2} = 25 sq. cm$$
Remaining area of circle = 53.57 cm<sup>2</sup>

4 A rectangular sheet of metal measures 8 cm and 6 cm. Four quadrants of circles each of radius 2 cm are cut away at corners. Find the area of the remaining portion.



Area of rectangular sheet =  $8 \times 6$ 

$$= 48 \text{ cm}^2$$

There are four quadrants of a circle, each of radius 2 cm cut away at the corners. Quadrant of circle means 1/4th of circle.

4 quadrant of circles = 4 x 
$$\frac{1}{4}$$
 of circle = 1 circle

Area of 4 quadrant circles = Area of one circle

$$=\pi r^2$$

$$=\frac{22}{7}\times2\times2$$

= 12.57 cm<sup>2</sup>

Area of remaining portion = Area of rectangular sheet – Area of four quadrant circles cut at corners.

= 48 - 12.57

Area of remaining portion =  $35.43 \text{ cm}^2$ 

#### 5 Find the perimeter of the given circular disc.



Sector:

r = 100 mm  
$$\theta$$
 = 360° - 45° = 315°

$$\ell = \frac{\theta}{360} \times 2\pi r \text{ unit}$$
$$= \frac{315}{360} \times 2 \times \pi \times 100 \text{ mm}$$

*l* = 550 mm

Perimeter of the given circular Disc =  $\ell$  + 2r

= 550 + 200 = 750 mm

#### Perimeter of the given circular Disc = 750 mm

### Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.3.06 Related problems of area of cut-out regular surfaces - circle, segment and sector of circle





## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.3.07 Area of irregular surfaces and application related to shop problems

#### Area of irregular surface

Surface area of irregular figures can be obtained by applying either, simpson's rule or trapezoidal rule. Area found by simpson's rule is more accurate than trapezoidal rule. However accurate area can be obtained if the number of ordinates are more i.e interval between ordinates is so small as possible. (Fig 1)



#### i Area as per simpson's rule

Area = 
$$\frac{h}{3} [(y_1 + y_7) + 4(y_2 + y_4 + y_6) + 2(y_3 + y_5)]$$

where

h = interval between ordinates

#### ii Area as per trapezoidal rule

Area = 
$$\frac{h}{2} [(y_1 + y_7) + 2(y_2 + y_3 + y_4 + y_5 + y_6)]$$

where

h = interval between ordinates

Calculate the area enclosed between the chain line, the edge and the end offsets by

#### The offsets were taken from a chain line to a edge.

Distance (M)	0	5	10	15	20	25	30	35
Off set (M)	4	3	2	5	1	2	3	5

(a) Simpson's rule

```
(b) Trapezoidal rule
```

#### (a) Simpson's rule

$$A = \frac{h}{3} [(y_1 + y_8) + 4(y_2 + y_4 + y_6) + 2(y_3 + y_{5+}Y_7)] \text{ unit}^2$$

$$A = \frac{5}{3} [(4 + 5) + 4(3 + 5 + 2) + 2(2 + 1 + 3)] \text{ m}^2$$

$$= \frac{5}{3} [9 + 4(10) + 2(6)]$$

$$= \frac{5}{3} [9 + 40 + 12]$$

$$= \frac{5}{3} \times 61 = 101.66$$

= 101.7 m<sup>2</sup>

#### (b) Trapezoidal rule

$$A = \frac{h}{2} [(y_1 + y_8) + 2(y_2 + y_3 + y_4 + y_5 + y_{6+}Y_7)] \text{ unit}^2$$

$$A = \frac{5}{2} [(4 + 5) + 2(3 + 2 + 5 + 1 + 2 + 3)] \text{ m}^2$$

$$= \frac{5}{2} [9 + 2(16)] \text{ m}^2$$

$$= \frac{5}{2} [9 + 32] \text{ m}^2$$

$$A = \frac{5}{2} \text{ x } 41 \text{ m}^2$$

$$= 102.5 \text{ m}^2$$

#### Calculation of the area of an irregular surface

In this Calculation the area of an irregular surface may be determined as follows.

In this method of calculation a chain line known as base line to be laid through the centre of the area of the surface.

The offset are taken to the boundary points in the order of their chainages on both the sides of the base line.

The chain line and offsets are noted down.

With reference to the notes the boundary points are plotted and the area to be divided into number of triangles and trapezium according to the shape.

#### Example

Now apply the geometrical formulae for calculation according to the shape of the figure. (Fig 1)



Chainline = AB

Offsets = C,E

1 Area of triangle

1/2 x base x height

2 Area of trapezium

$$\frac{\text{base } (a+b)}{2} \times \text{height}$$
#### Example

#### Plot the following details of a field and calculate its area (all measurements are in metres) (Fig 1)



Serial No. 1 In  $\Delta$ AB

Chainage in metres  $\,$  0 and 20m.

Offsets in metres 0 and 36m.

 $\ln \ \Delta \, {\rm ABI}$ 

Area =  $\frac{1}{2}$  x base x height

=1/2 x 20 x 36

=360 sq.m

#### SI. No. 2

Area of trapezium IBCK

Chainage in metres = 20m and 55m = 35m Offsets in metres 36m and 20m = 28m

$$= \frac{(a+b)}{2} \times \text{height} = \left[\frac{36+20}{2} \times 35\right]$$
$$= 28 \times 35 = 980 \text{ sq.m}$$



SI. No. 4

Area of triangle KCD

 $= \frac{1}{2} x b x h = \frac{1}{2} \times 20 \times 45$ = 45m x 10m = 450 Sq.m

Area of rectangle DEFL = 25 x 30 = 750 sq.m **SI. No. 5 (LFGJ)** 

Area of Trapezium LFGJ = 
$$\frac{(a+b)}{2} \times \text{height} = \left[\frac{30+35}{2} \times 30\right]$$
  
= 32.5m x 30m = 975 sq.m

SI. No. 6

Area of trapezium AJGH =  $\frac{35+45}{2} \times 35 = \frac{80}{2} \times 35$ = 40 x 35 = 1400 sq.m

S. No.	Figure	Chainline in metres	Base in Metres	Offsets in metres	Mean offsets in metres	Area in s Metres	quare	Remarks
						+ve	-ve	
1	2	3	4	5	6	7	8	9
1	ΔΑΒΙ	0 and 20	20	0 and 36	18	360		
2	Trapezium IBCK	20 and 55	35	36 and 20	28	980		
3	∆KCD	55 and 100	45	0 and 20	10	450		
4	Rectangle DEFL	100 and 75	25	0 and 30	15	750		
5	Trapezium LFGJ	75 and 45	30	30 and 35	32.50	975		
6	Trapezium JGHA	45 and 0	45	45 and 35	40 Total	1400 4915		
					TOtal	4010		

## Assignment

Calculate the area of the irregular surfaces given below.



Note : All dimension are in mm.

# Elasticity - Elastic, plastic materials, stress, strain and their units and young's modulus

#### **Elastic material**

The Elastic materials are those materials that have the ability to resist a distorting or deforming influence or force, and then return to their original shape and size when the same force is removed.

Linear elasticity is widely used in the design and analysis of structures such as beams, plates and sheets.

Elastic materials are of great importance to society since many of them are used to make clothes, tires, automotive spare parts, etc.

#### **Characteristics of elastic materials**

When an elastic material is deformed with an external force, it experiences an internal resistance to the deformation and restores it to its original state if the external force is no longer applied.

To a certain extent, most solid materials exhibit elastic behavior, but there is a limit of the magnitude of the force and the accompanying deformation within this elastic recovery.

A material is considered as elastic if it can be stretched up to 3 times of its original length.

For this reason there is an elastic limit, which is the greatest force or tension per unit area of a solid material that can withstand permanent deformation.

For these materials, the elasticity limit marks the end of their elastic behavior and the beginning of their plastic behavior. For weaker materials, the stress or stress on its elasticity limit results in its fracture.

The elasticity limit depends on the type of solid considered. For example, a metal bar can be extended elastically up to 1% of its original length.

However, fragments of certain gummy materials may undergo extensions up to 10 times. The elastic properties of most solid intentions tend to fall between these two extremes.

Maybe you might be interested How to Synthesize an Elastolic Material?

#### Examples of elastic materials

- 1 Natural gum
- 2 Spandex or lycra
- 3 Butyl Rubber (GDP)
- 4 Fluoroelastomer
- 5 Elastomers
- 6 Ethylene-propylene rubber (EPR)
- 7 Resilin
- 8 Styrene-butadiene rubber (SBR)
- 9 Chloroprene

- 10 Elastin
- 11 Rubber Epichlorohydrin
- 12 Nylon
- 13 Terpene
- 14 Isoprene Rubber
- 15 Poilbutadiene
- 16 Nitrile Rubber
- 17 Vinyl stretch
- 18 Thermoplastic elastomer
- 19 Silicone rubber
- 20 Ethylene-propylene-diene rubber (EPDM)
- 21 Ethylvinylacetate (EVA or foamy gum)
- 22 Halogenated butyl rubbers (CIIR, BIIR)
- 23 Neoprene
- **Plastic Material**

#### **Plastic Material Classification**

"Plastic material" is a term that refers to a large class of polymers, separated into various groups and sub-groups. Before starting the chapter on the uses and subsequent recycling of plastic, let us establish a general classification of these thermosetting resins or thermo-plastics (the two big groups into which we include elastomers) by detailing their properties, their make-up, their aspect, and their final uses, while explaining which ones are recyclable.

#### Thermoplastics

Remember that thermoplastic is a material whose structure and viscosity can be modified both ways through heating or cooling. This large family of materials is commonly used by many industries and is easily integrated into France's recycling cycles.

The following polymers are some examples of plastic material:

- 1 Polyolefins
- 2 Vinyl polymers
- 3 Polystyrenes
- 4 Acrylate and methacrymate polymers
- 5 Polyamide
- 6 Polycarbonates
- 7 Celluloid
- 8 Linear polyesters
- 9 Polyfluorethane
- 10 Polyacetal
- 11 Polysulfone

- 12 Polyphenylene sulfide
- 13 Modified polyphenylene oxide (PPO)

#### **Thermosetting plastic**

Thermosetting plastic is a compound that, during condensation polymerisation and/or implementation, when submitted to a catalyst or a temperature increase, irreversibly cures. the structure, shape, or rigidity of the manufactured plastic object can not be modified again, and the material is rarely recycled.

This type of plastic includes the following types of compounds:

- 1 Unsaturated polyster
- 2 Phenol formaldehyde resins
- 3 Melamine resins
- 4 Polyepoxides
- 5 Polyimide
- 6 Polyurethane
- 7 Polyorganosiloxanes

Generally in any industry the material used are elastic in nature. Hence if a material is subjected to an external load, it undergoes deformation. During the deformation process the material will offer a resistance against the deformation. In case if the material fails to put up full resistance to the external load, the deformation continues until rupture takes place. Hence it is important to have a considerable knowledge about the materials and their properties for designing and fabricating.

#### Force

Force is defined as an external source which changes or tends to change the state of rest or of uniform motion of an object. In other words everybody preserves in its state of rest or of uniform motion unless it is forced by an external source to change that state. That external source is called as Force. It has both magnitude and direction. So it is a vector quantity. In SI system, its unit is Newton.

Unit in MKS - kgf

1 kgf = 9.81 Newton

Force is defined as the product of mass of the object and the acceleration.

Force = mass x acceleration

- F = m x a
  - = Kg x m/sec<sup>2</sup>
  - = 1 Newton

#### **Causes of force**

- Change in speed
- Change in direction
- Change in shape
- Change in dimension
- Change in condition (Rest to uniform motion and vice versa)

#### Types of forces

- tensile force
- compressive force
- shear force.

**Tensile force:** When two equal and opposite forces act on a body and have the same line of action, and if they tend to increase the length of the body, the applied forces are called tensile forces. (Fig 1)



**Compressive force:** When two equal and opposite forces act on a body having the same line of action and if they tend to compress the body and try to reduce the length of the body, the forces applied are called compressive forces. (Fig 2)



**Shear force:** When two equal and opposite forces having different lines of action act on a body such that one section of the body tends to slide over another section which results in a shearing action then the forces are referred to as shear forces. (Fig 3)



**Direct effect of forces:** Forces acting on a body can cause in the material. (Fig 4 & Fig 5)



- Tension
- Compression
- Shearing effect
- Twisting effect
- Bending effect.

Force is mainly classified as tensile force, compressive force and shear force.

#### Stress

The internal opposite force to the external load per unit area is known as stress. The unit of stress depends upon the force applied and area of original cross-section of material.

$$\therefore \text{ Stress} = \frac{\text{Forced applied}}{\text{Area of original cross section}}$$

$$=\frac{\text{Load}(\text{or})\text{Force}}{\text{Area}}\left(\frac{\text{N}}{\text{mm}^2}\text{ or }\frac{\text{Kg}}{\text{cm}^2}\right)$$

Shear stress = 
$$\frac{F}{A} \left( \frac{N}{cm^2} \text{ or } \frac{Kg}{cm^2} \right)$$

#### **Types of Stress**

- 1 Tensile stress
- 2 Compressive stress
- 3 Shear stress
- 4 Torsional Stress
- 1 **Tensile stress:** When a material is subjected to two equal and opposite axial pulls, the material tends to increase in length. The resistance offered against this increase in length is called tensile stress. The corresponding strain is called tensile strain. (Fig 6)



#### E.g.:

- 1 When brake is applied the brake rod is under tensile stress.
- 2 During tightening of bolt or nut.
- 3 Belt driving motor.
- 4 Crane rope (When rope is pulling)
- 2 **Compressive stress:** When a material is subjected to two equal and opposite axial pushes, the material tends to decrease in length. The resistance offered against

the decrease in length is called compressive stress. The corresponding strain is called compressive strain. (Fig 7)



Eg.

- 1 Compressive stress on connecting rod on the first part of power stroke
- 2 Compressive stress on push rod during valve opening
- 3 Clutch lining when the clutch is engaged
- 3 Shear stress: When a material is subjected to two equal and opposite forces acting tangentially across the resisting section, the body tends to be sheared off across the cross section. The stress included is called shear stress. It is represented by  $\tau$ . The corresponding strain is called shear strain. (Fig 8)



Shear stress = 
$$\frac{F}{A} \left( \frac{N}{cm^2} \text{ or } \frac{Kg}{cm^2} \right)$$

- Eg.
- 1 Rivets
- 2 Gudgeon Pin
- 3 Spring shackle pin
- 4 Brake rod rivets
- 5 Chassis rivets
- 6 Fly wheel holding bolts
- 7 Swivel pins
- 8 Gear box shaft
- 9 Axle shaft

**4 Torsional stress:** When a shaft is subjected to the action of two equal and opposite couples acting in parallel planes, then the shaft is said to in torsion. The stress set up by the torsion is known as torsional shear stress.

Eg.

- 1 Rear axle
- 2 Crank shaft
- 3 Coil springs
- 4 Propeller shaft
- 5 Starter motor armature shaft

#### Examples

1 A steel wire 3 mm dia. is loaded in tension with a weight of 50 kg. Find out the stress developed.

Diameter of the steel wire = 3 mm

Stress = 
$$\frac{Force(F)}{Area(A)}$$

Area of circular wire (A) = 
$$\pi r^2$$
 unit<sup>2</sup>

$$=\frac{22}{7} \times 1.5 \times 1.5$$
$$=\frac{49.5}{7} = 7.07 \text{mm}$$

Stress = 
$$\frac{50}{7.07}$$

= 7.072 Kg/mm<sup>2</sup>

2 A force of 500 N is applied on a metallic wire of 5mm diameter. Find the stress.

Diameter of the wire	= 5 mm	
Radius	= 2.5 mm	

Stress = 
$$\frac{Force(F)}{Area(A)}$$

Area of circular wire (A) =  $\pi r^2$  unit<sup>2</sup>

$$=\frac{22}{7} \times 2.5 \times 2.5$$
  
=  $\frac{137.5}{7} = 19.64 \text{mm}^2$   
Stress =  $\frac{500}{19.64}$ 

3 A load of 600 kg is placed on a hollow cast iron cylinder of 200 mm outer diameter and 100 mm internal diameter. Find the stress on the cylinder.

#### Hollow cylinder

Outer diameter (D) = 200 mm = 20 cm  
Outer radius (R) = 10 cm  
Internal diameter (d) = 100 mm = 10 cm  
Inner radius (r) = 5 cm  
Weight = 600 kg  
Stress = 
$$\frac{Force(F)}{Area(A)}$$
  
Area =  $\pi (R+r)(R-r)$   
 $= \frac{22}{7} \times (10+5) \times (10-5)$   
 $= \frac{22}{7} \times 15 \times 5$   
 $= \frac{1650}{7} = 235.7 cm^2$   
Stress =  $\frac{600}{235.7} kg/cm^2$ 

= 2.546 kg/cm<sup>2</sup>

Calculate the minimum cross section area of a M.S. bar to withstand a load 6720 kg. Take the maximum stress of the material as 698.2 kg/cm<sup>2</sup>.

Weight = 6720 kg  
Maximum stress = 698.2 kg/cm<sup>2</sup>  
Stress = 
$$\frac{Force(F)}{Area(A)}$$
  
Area(A) =  $\frac{6720}{698.2}$   
= 9.625 cm<sup>2</sup>  
To calculate diameter  
Area =  $\frac{\pi d^2}{4}$  unit<sup>2</sup>  
d<sup>2</sup> = 4 x 9.625 x  $\frac{7}{22}$   
=  $\frac{134.75}{11}$   
d<sup>2</sup> = 12.25  
d = 3.5 cm

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2nd Year : Exercise 2.4.08

5 A load of 300 kg hanging from a rod of 3 metre length and 5 mm diameter extends it by 4 mm. Find the stress in the material and the strain it causes.

	Length of the rod	= 3 m = 3000 mm
	Increased length	= 4 mm
	Diameter	= 5 mm;
	Radius	= 2.5 mm
	Weight	= 300 kg
	Strain	= Change in length Original length
		$=\frac{4}{3000}=0.00133$
	Stress	$= \frac{Force(F)}{Area(A)}$
Ar	ea of circular rod (A)	= $\pi r^2$ unit <sup>2</sup>
		$=\frac{22}{7}\times2.5\times2.5$
		$=\frac{137.5}{7}$
		= 19.643 mm <sup>2</sup>
	Stress	$=\frac{300}{19.643}$
		= 15.273 kg/mm <sup>2</sup>
6	Find the force required dia. in a 1 mm thick stress is 50 N/mm <sup>2</sup> .	ired to punch a hole of 10 mm k plate, if the allowable shear
	Thickness of the plat	e = 1 mm
	Dia. of the punch	= 10 mm
	Shear stress	= 50 Newton/mm <sup>2</sup>

- Force = Shear stress x area
- Shear area

6

 $= \pi dt$  $=\frac{22}{7} \times 10 \times 1$  $=\frac{220}{7}=31.43$  mm<sup>2</sup> = 50 x 31.43

= Circumference x thickness

= 1571.5 Newtons

- Thickness of the plate = 5 mm = 0.5 cmDiameter of the punch = 30 mm = 3 cm = 400 kg/cm<sup>2</sup> Shear stress Force = Shear stress x area Shear area = Circumference x thickness  $= \pi dt$  $=\frac{22}{7} \times 3 \times 0.5$  $=\frac{33}{7}=4.71$  mm<sup>2</sup> Required force = 400 x 4.71 = 1885.71 kg
- 8 What force will be required to shear off a bar of 30 mm dia. if the ultimate shear stress of the material is 35 kg/mm<sup>2</sup>.

Required Force	e = 24750 kg
F	= 35 x $\pi$ x 15 x 15 kg
35	$=\frac{F}{\pi\times 15\times 15}$
Stress	$= \frac{\text{Force}(F)}{\text{Area}(A)}$
Shear stress	= 35 kg/mm <sup>2</sup>
Diameter of the bar	= 30 mm

9 A Hole of 2 cm dia is to be punched out of a plate of 1.4 cm thick. If the force applied to the punching die is 12 KN. Calculate the shear stress.

Dia. of the hole	= 2cm
Thickness	= 1.4 cm
Force	= 12 KN
Shear stress	= ?
Punched out area	= Circumference of the hole $\times$ Thickness
	= 2 $\pi$ r × t unit <sup>2</sup>
	= $2 \times \pi \times 1 \times 1.4$
	= 2.8 $\pi$ cm <sup>2</sup>
Shear stress	$=\frac{F}{A}$
	$=\frac{12KN}{2.8\picm^2}$
Shear stress	= 1.364 KN/cm <sup>2</sup>

7 A hole of 30 mm diameter is punched in a plate of 5 mm thickness. If the shear stress is 400 kg/cm<sup>2</sup>. Find the force required to punch the hole.

Force

#### 10 A square rod of 10 mm side is tested for a tensile load of 1016 kg. Calculate the tensile stress?

Side of square rod (a)	= 10 mm
Tensile force (F)	= 1016 kg
Tensile stress ( $\sigma$ )	= ?

Stress

$$= \frac{\text{Force}}{a^2}$$
$$= \frac{1016}{10 \times 10}$$

Force(F)

Tensile stress = 10.16 Kg/mm<sup>2</sup>

11 A M.S. tie bar 3.5 cm dia. is under a state of stress which carries a load of 6720 kg. Find the intensity of stress in the material.

d = 3.5 cm  
r = 1.75 cm  
F = 6720 kg  
Stress = 
$$\frac{Force(F)}{Area(A)}$$
  
=  $\frac{Force}{\pi r^2}$ 

$$=\frac{6720}{3.14 \times 1.75 \times 1.75}$$

$$=\frac{6720}{9.616}$$

Intensity of stress = 698.8 Kg/cm<sup>2</sup>

## 12 A rivet of 10 mm dia. is subjected to a double shear force of 1.5 KN. Find the shear stress in the rivet.

dia. of the rivet = 10 mm r = 5 mm Shear stress = ?

Double shear force is acting on the rivet, consider the area as double.

Stress

$$=\frac{1.5}{2x3.14x5x5}$$

= 0.00955 KN/mm<sup>2</sup>

Shear stress

When an external forces acting on a material, there is a change in its dimension and shape. The deformation is called strain. Thus, strain is the ratio between the change in dimension of a material to its original dimension. It has no unit. It is represented by E (Epsilon)

Strain = 
$$\frac{\text{Change in dimension } (\delta \ell)}{\text{Original dimension } (\ell)}$$

#### Linear or Longitudinal strain

It is the ratio between the change in length of the material to its original length.

Linear Strain = 
$$\frac{\text{Change in length } (\delta \ell)}{\text{Original length } (\ell)}$$

#### Lateral Strain

It is the ratio between change in cross sectional area of material to its original area.

#### Volumetric Strain

It is the ratio between change in volume of material to its original volume.

rain = Change in volume Original Volume

#### **Poisson's ratio**

It is a ratio between lateral strain and linear strain.

Poisson's ratio = 
$$\frac{\text{Lateral strain}}{\text{Linear strain}} = \frac{1}{m}$$

#### Examples

1 Calculate the tensile strain when a force of 3.2 kN is applied to a bar of original length 280 cm extends the bar by 0.5 mm (Fig 1 & Fig 2)

Tensile strain = 0.0001786



2 A steel rod used for brake operation is 1.50 m long. When it is subjected to a tensile force the extension produced is 0.5 mm. Find the strain in the rod.



	0.5	(mm)
=	1.5 x 1000	(mm)



3 A helical spring is loaded with a force of 600 Newton and is compressed by 30mm. What would be the load required to compress it to 10 mm. (Fig 3)

Solution

$$= \frac{600}{30} \left( \frac{N}{mm} \right) = 20 \left( \frac{N}{mm} \right)$$

Load required to compress the spring by 10 mm

= spring stiffness x compression

= 20 (N/mm) x 10(mm)

Load required = 200 N



4 Helical spring is loaded with a force of 400 Newton and it is compressed by 18 mm. What would be the load required to compress it to 6 mm?

Given force	= 400 Newton	
Deflection	= 18 mm	
Spring Stiffness	= Force / Compressed length	
	= 400 /18	
	= 22.22 Newton / mm	
Force required to compress the spring into 6 mm	= Spring stiffness × Compression	
Load required	= 22.22 × 6	
	= 133.32 N	

5 Calculate the tensile strain when a force of 3.2 KN is applied to a bar of original length 2.8 m extends the bar by 0.5 mm.

Tensile strain	= 0.0001786
	$=\frac{0.05}{280}$
Strain	$=\frac{\Delta\ell}{L}$
Tensile strain	= ?
Increased length( $\Delta \ell$ )	= 0.5 mm = 0.05 cm
Original length L	= 280 cm
Force F	= 3.2 KN

6 A metal bar is 2m long. When 5.5 tonne is applied its length becomes 1.995 m. Find the compressive strain?

Force F	= 5.5 KN		
Original length L <sub>1</sub>	= 2 m		
Final length L <sub>2</sub>	= 1.995 m		
Increased length( $\Delta \ell$ )	= 2 - 1.995 = 0.005 m		
Compressive strain	$=\frac{\Delta \ell}{L}$		
	$=\frac{0.005}{2}$		
Compressive strain = 0.0025			

7 When a steel rod of 4mm diameter experienced the load of 200 Kg. It is found to be elongated by 1.5 mm from the original length of 1500 mm. Calculate the strain.

strain	= 0.001
	= 1500
	1.5
strain	$=\frac{\Delta \ell}{L}$
Strain	= ?
$\Delta \ell$	= 1.5 mm
Original length $L_1$	= 1500 mm
Force F	= 200 Kg.

8 An iron rod of length 1 metre and 1 cm diameter gets elongated by 1 cm. When a force of 100 Kg is applied at one end. Calculate the strain developed in the rod.

Force F = 100 Kg. Original length L<sub>1</sub> = 1 m = 100 cm  $\Delta \ell$  = 1 cm

> Strain = ? strain =  $\frac{\Delta \ell}{L}$ =  $\frac{1}{100}$

#### Compressive strain = 0.01

#### **Elasticity and Elastic limit**

When an external force acts on a body, the body tends to under go some deformation. If the external force is removed and the body comes back to its original shape and size (Which means the deformation disappears completely). The body is known as elastic body. This property by virtue of which certain materials return back to their original position after the removal of the external force is called elasticity.

The body will regain its previous shape and size only when the deformation caused by the external force is with in a certain limit. Thus there is a limiting value of force up to and within which the deformation completely disappears on the removal of the force. The value of stress corresponding to this limiting force is known as elastic limit of the material.

If the external force is so large that the stress exceeds the limit, the material loses to some extent its property of elasticity. If now the force is removed, the material will not return to its original shape and size and there will be a residual deformation in material.

#### **Yield point**

The yield point of a material is the point at which there is a marked increase in elongation without increase in load.

#### Hooke's law

Robert Hooke discovered a relationship between stress and strain. According to Hooke's law stress is proportional to strain within elastic limit.

#### Young's Modulus or Modulus of Elasticity

The ratio of stress to strain within elastic limit is known as young's modulus or modulus of elasticity. This is expressed by a symbol "E". The unit of Young's modulus is same that of stress.

Young' s modulus (E) = 
$$\frac{\text{Stress}}{\text{Strain}}$$

#### Modulus of Rigidity

.

The ratio of shear stress to shear strain is known as "modulus of rigidity" represented by symbol "N".

$$\therefore \quad \text{Modulus of Rigidity (N)} = \frac{\text{Shear stress}}{\text{Shear strain}}$$

#### **Bulk Modulus**

When a body is subjected to three mutually perpendicular forces of the same intensity, the ratio of volumetric stress to the volumetric strain is known as Bulk Modulus. It is usually represented by the letter K.

Bulk Modulus (K) = 
$$\frac{\text{Volumetric stress}}{\text{Volumetric strain}}$$

## Relationship between three moduli for a given material

The relationship between three moduli for a given material is as follows :

$$E = 2N\left(1 + \frac{1}{m}\right) = 3 K\left(1 - \frac{2}{m}\right).$$

Where 4500 π×6.25 E = Young's modulus of elasticity N = Modulus of rigidity K = Bulk modulus  $=\frac{4500\times4}{\pi\times6.25}$  $\frac{1}{m}$  = Poisson's ratio  $=\frac{2880}{\pi}$ Example 1 A steel rod of 10 mm diameter and 175 mm long Stress =  $\frac{2880}{\pi}$ Kg/cm<sup>2</sup> ... is subjected to a tensile load of 15 kN. If E = 2 x10<sup>5</sup> N/mm<sup>2</sup>, calculate the change in length. Strain =  $\frac{Change in length}{Original length}$ **Tensile** load = 15 kN = 15000 N • Area of cross section =  $(\pi r^2) = \frac{22}{7} \times 5 \times 5 \text{ mm}^2 = 78.57$  $=\frac{0.008}{20}=\frac{8/1000}{20}$ Stress =  $\frac{15000N}{0.785 \times 100 \text{ mm}^2}$  = 191 N/mm<sup>2</sup>  $=\frac{8}{20\times1000}=\frac{4}{10000}$ *.*.. Strain =  $\frac{4}{10000}$ Young's modulus E = Stress ... Strain  $E = 2 \times 10^5 \text{ N/mm}^2 = \frac{191 \text{N/mm}^2}{\text{Strain}}$ \_ Stress · Young's modulus Strain Strain =  $\frac{191}{2 \times 10^5}$  $=\frac{2880}{\pi}\div\frac{4}{10000}$ ...  $=\frac{2880}{\pi}\times\frac{10000}{4}$ Change in length =  $\frac{175 \times 191}{2 \times 10^5}$  mm  $=\frac{7200000}{\pi}$ = 0.167 mm. 2 A bar of steel 2.5 cm diameter was subjected to = 2292000 Kg/cm<sup>2</sup> compressive load of 4500 kg. The compression in

- = 2.292 x 10<sup>6</sup> Kg/cm<sup>2</sup>
- 3 A force of 10 tonnes is applied axially on a rod of 12 cm dia. the original length is 100 mm.lf modulus of elasticity is 2 x 10<sup>12</sup> kg/cm<sup>2</sup>. Calculate stress and strain developed in the rod.

#### Solution

Force applied = 10 tonnes = 10 x 1000 kg  
= 
$$10^4$$
 kg  
Diameter (d) = 12 mm = 1.2 cm  
Young's modulus (E) = 2 x  $10^{12}$  kg/cm<sup>2</sup>

Stress = 
$$\frac{\text{Force applied}}{\text{Area of original cross section}}$$
$$= \frac{4 \times 10^4}{10^4}$$

 $\pi \times 1.2 \times 1.2$ 

Force applied Stress = Area of original cross section

a length of 20 cm was found to be 0.008 cm. Find

= 0.008 cm

 $=\frac{\pi}{4}\times 2.5^2$ 

 $= \frac{\pi \times 6.25}{4} \text{ cm}^2$ 

the Young's modulus of elasticity of bar.

Force applied i.e. compressive load = 4500 kg

Diameter of bar (d) = 2.5 cm

Original length of bar = 20 cm

:. Area of original cross-section =  $\frac{\pi}{4} d^2$ 

Change in length

Solution

.:.

$$\begin{aligned} &= \frac{10^4 \times 4}{1.2 \times 1.2 \times 3.142} \\ &= \frac{40000}{452.45} \\ &= 8639 \text{ kg/cm^2} \end{aligned} \\ &= 8639 \text{ kg/cm^2} \end{aligned} \\ &= 8639 \text{ kg/cm^2} \end{aligned} \\ &= 110300 \text{ kg/cm^2} \end{aligned} \\ &= 11000 \text{ kg/cm^2} \end{aligned} \\ &= 11000 \text{ kg/cm^2} \end{aligned} \\ &= \frac{8399}{2 \times 10^{12}} \end{aligned} \\ &= \frac{8399}{2 \times 10^{12}} \end{aligned} \\ &= \frac{4419.5}{10^{12}} \end{aligned} \\ &= \frac{4419.5}{10^{12}} \end{aligned} \\ &= \frac{4419.5 \times 10^{12}}{10^{12}} \end{aligned} \\ &= \frac{4419.5 \times 10^{12}}{10^{12}} \end{aligned} \\ &= \frac{11}{2} \text{ cm} \end{aligned} \\ &= \frac{110}{2} \text{ cm} \end{aligned} \\ &= \frac{11$$

WCS : TDM (Dies & Moulds) : (NSQF - Revised 2022) - 2<sup>nd</sup> Year : Exercise 2.4.08

 $=\frac{2000}{\pi r^2}$ 

 $=\frac{1.36}{100}$ 

= 0.0136

*:*..

4

	=	Stress(a)	= Force(F) $=$ Force
	3.14 x 0.8 x 0.8	01635(0)	Area(A) Ixb
	$= \frac{2000}{2.0096}$ = 995.2 kg/cm <sup>2</sup>		$= \frac{2000}{2 \times 1}$ = 1000 kg/cm <sup>2</sup>
Young's modulus	= Stress Strain	E	= $\frac{\text{Stress}}{\text{Strain}}$
2 x 10 <sup>6</sup>	= <u>995.2</u> Strain	2 x 10 <sup>6</sup>	= $\frac{1000}{\text{Strain}}$
Strain	$=\frac{995.2}{2 \times 10^6}$	Strain	$=\frac{1000}{2 \times 10^6}$
	= 0.0005		= 0.0005
7 A tensile load of rectangular rod of 2 metres. Calculate t 2 x 10 <sup>6</sup> Kg/cm <sup>2</sup> .	f 2000 kg is applied on a 2 cm x 1 cm whose length is 2 he elongation in length as E =	$\frac{\Delta \ell}{L_1}$ $\frac{\Delta \ell}{\Delta \ell}$	= Strain = 0.0005
F	= 2000 Kg.	200	
L <sub>1</sub>	= 2 m = 200 cm	Â	= 200 x 0.0005
E	= 2 x 10 <sup>6</sup> kg/cm <sup>2</sup>		= 0.1 cm
Rectangular rod lengt	h = 2 cm	.: Elongated length	n = 0.1 cm

Breadth = 1 cm

### Assignment

#### Stress

- 1 Calculate the intensity of stress in the material if a copper rod of 40 mm diameter is subjected by tensile load of 4000 Newton's.
- 2 Calculate the intensity of stress if a mild steel rod having a cross sectional area of 40 mm<sup>2</sup> is subjected to the load of 1000 kg.
- 3 Calculate the tensile stress if a square rod of 10 mm side is tested for a tensile load of 1000 kg.
- 4 Calculate the maximum stress if a bar of 9 cm<sup>2</sup> cross sectional area and 300 cm long carries a tensile load of 3500 kg.
- 5 Find out the stress on the rod. if a load of 500 kg is placed on a M.S.rod of dia. 35 mm.
- 6 A metallic bar of 8 cm diameter is under stress carrying a load of 8620 N. Calculate the intensity of stress.
- 7 A steel wire 2 mm diameter is loaded in tension with a weight of 20 kg. Find out the stress developed.

- 8 A rod having a cross sectional area of 25 mm<sup>2</sup> is subjected to a load of 1500 kg. Find out stress on the rod.
- 9 A square rod of 10 mm side is tested for a tensile load of 2500 kg. Calculate the tensile stress of the rod.

#### Strain

- 1 Find the compressive strain if a metal bar is 150 cm long. When 2.5 KN is applied, its length becomes 148.6 cm.
- 2 Calculate the strain if a metallic bar is 150 cm long. When 2500 kg is applied its length becomes 150.5 cm.
- 3 Find the strain it causes if a load of 300 kg hanging from a rod of 3 metres length and 5 mm diameter extends it by 4 mm.
- 4 A tensile force of 10 kg is applied on a copper wire of diameter 1 cm. So that the length of wire increases by 5 mm. If the original length of wire was 2 metres, find out the strain.

- 5 A steel rod whose diameter is 1 cm and 60 cm in length. This rod is pulled at both ends by a force of 700 kg. If modulus of elasticity of steel is  $2.1 \times 10^6$  kg/cm<sup>2</sup>, find out increase in length of rod and strain produced in it.
- 6 A steel rod 1.5 metres long and of 30 mm diameter is pulled at both ends by a force of 1500 kg. If modulus of elasticity of steel is  $2.4 \times 10^6$  kg/cm<sup>2</sup>, determine increase in length of rod and strain produced in it.
- 7 Calculate the change in length of a rod of dia 16 mm and 160 mm long when it carries a load of 40KN. Take E =  $200000 \text{ N/mm}^2$ .
- 8 A hollow C.I. column with a wall thickness of 2 cm is subjected to an axial compressive load of 80 tonnes. If the maximum stress is not to be exceeded 1 tonne per cm<sup>2</sup>, determine the internal diameter of column. Calculate compressive strain, if E = 950 tonnes per cm<sup>2</sup>.

#### Young's modulus

- 1 A piece of wire 2 m long, 0.8 mm<sup>2</sup> in cross section increases its length by 1.6 mm on suspension of 8 kg weight from it. Calculate the stress, strain and young's modulus.
- 2 A wire of 16 mm dia. is subjected to a tensile load of 2000 kg. Find the stress and strain if young's modulus  $E = 2 \times 10^{16} \text{ kg/cm}^2$ .
- 3 A wire of 2 metres long and its area of cross section is 0.78 mm<sup>2</sup>. If 78 kg weight is suspended on this wire, then the length of the wire is increased by 1.4 mm. Find out stress, strain and young's modulus of elasticity.

- 4 A wire 2800 mm long is stretched by 0.5 mm, when a weight of 9 kg is hung on it, its diameter is 2 mm. Calculate stress and young's modulus for the substance of the wire.
- 5 A force of 1000 kg is applied axially on rod of 12 mm diameter the original length is 100 mm. If modulus of elasticity is  $2 \times 10^{12}$  kg/cm<sup>2</sup>. Calculate the stress and strain developed in the rod.
- 6 A steel wire 3.2 mm diameter and 3.65 metre long stretches by 2.03 mm under the load of 115 kg. Calculate the stress and young's modulus of elasticity.
- 7 A mass of 10 kg is hung from a vertical wire 300.25 cm long and 0.0005 sq. cm cross section. When the load is removed the wire is found to be 300 cm long. Find the modulus of elasticity for the wire material.
- 8 A steel rod of 1.5 cm diameter and 8 metres long pulled by a forced of 80 kg at both ends. Find out the expansion and strain on the rod. The coefficient of elasticity  $E = 2.10 \times 10^6$  kg/cm<sup>2</sup>.
- 9 A wire of length 3.5 m and diameter 0.35 mm is stretched by a force of 2kg weight. If the elongation is 4 mm. Calculate the young's modulus of the material of wire.
- 10 A mass of 1kg is suspended from a metal wire 100 cm long and 0.5 mm diameter. An increase in length of wire equal to 2 mm is observed. Calculate the young's modulus of wire.
- 11 A 4 metre long copper wire of diameter 3 mm is used to support a mass of 50kg. What will be the elongation of the wire. Young's modulus of elasticity for copper is 7x10<sup>10</sup> N/mm<sup>2</sup>.

## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.4.09

### Elasticity - Ultimate stress and working stress

#### **Ultimate stress and Working stress**

The minimum load at which a material develops failure is called as ultimate load or breaking load. The stress produced in a material at ultimate load is called as ultimate stress or breaking stress.

 $\therefore \quad \text{Ultimate stress} = \frac{\text{Ultimate load}}{\text{Area of original cross section}}$ 

The load which is considered safe for the machine element is known as safe load or working load and the corresponding stress at this load is called as safe stress or working stress.

∴ Safe stress= Safe load Areaoforiginal cross section

#### Factor of safety (Fig 1)



The ratio of ultimate stress to working stress (i.e. safe stress) is known as factor of safety. The ratio of ultimate load to the safe load may also be termed as factor of safety. It has no unit. Hence it is expressed in a number.



Factorofsafety=Ultimate load

#### Stress-Strain graph

#### Load-extension graph (Fig 2)



A metal (say mild steel) is subjected to increasing load and the extensions are measured with an extensometer. On plotting a graph between the loads and elongations produced, in the beginning, there is a straight-line relationship. It continues up to 'a' which is called the limit of proportionality, i.e. up to 'a' in Fig 2 'Stress is proportional to strain'.

Point b denotes the elastic limit. Below this point, the body regains its original shape, if the load is removed. Beyond this point the body does not recover its original shape completely, even if the load is removed.

Upto a point beyond the elastic limit, a considerable amount of elongation takes place even with a slight increase in load. The point C where it occurs, is called the yield point.

At 'd' the maximum or the ultimate load is reached. After this, a waist or local contraction is formed in the specimen, and fracture occurs as illustrated in Figure.

A standard steel bar of 30 mm square cross section is subjected to tensile stress. If the factor of safety is 4 and ultimate stress is  $370 \text{ N/mm}^2$  determine the load to which the bar is subjected. (Fig 3)



Working stress =  $\frac{370}{4}$  N/mm<sup>2</sup> = 92.5 N/mm<sup>2</sup>

Area of cross section = 900 mm<sup>2</sup>

$$(a^2 = 30^2 = 900, a = \sqrt{900} = 30)$$

Load = Working tensile stress x area

= 900 mm<sup>2</sup> x 
$$\frac{370}{4}$$
 N/mm<sup>2</sup>  
= 83250 N

#### Example

1 A rod of Ø60 mm is subjected to a maximum tensile load of 1600 kg. Calculate the stress and strength of the material. If the factory of safety is 5.

Dia. of rod	(d)	= 60 mm
Tensile load	(F)	= 1600 kg

		F_ 1600	Factor of safety (FS	) = 4
I	Stress	$=\frac{1}{A}=\frac{1}{\pi\times 30\times 30}$	ES	_ Ultimate stress
		= 0.5658 kg/mm² Ans.	F <b>3</b> .	Working stress
ii	Factor of safety	= 5		25kg/mm <sup>2</sup>
	Factor of safety	= Ultimate stress	4	=
	i dotor or oaroty	Working stress	14/2	25
		5Ultimate stress	VVS	$=$ $\frac{1}{4}$ kg/mm <sup>2</sup>
		0.5685 kg/mm <sup>2</sup>		= 6.25 kg/mm <sup>2</sup>
	Ultimate stress	= 5 × 0.5658 kg/mm²	Stress	_ <u>F</u>
	Strength of the	material = 2.829 kg/mm <sup>2</sup>	011633	Ā
2	Find the safe loa a 4.2 mm dia. wi	ad which can be suspended from re. If the ultimate stress is 25 kg/	6.25 kg/mm <sup>2</sup>	$=\frac{Fkg}{\pi\times 2.1\times 2.1mm^2}$
			F	= $6.25 \times \pi \times 2.1 \times 2.1$ kg
	Dia. of wire d	= 4.2 mm	Safe load F	= 86.6 kg
	Ultimate stress L	$J.S = 25 \text{ kg/mm}^2$		

### Assignment





Ultimate tensile strength = 370 N/mm<sup>2</sup> Shear force = 380 kN R = 30 mm Thickness of plate punched = \_\_\_\_ mm Ultimate tensile strength = 330 N/mm<sup>2</sup>







Ultimate tensile strength = 220 N/mm<sup>2</sup>

(Shear force)

mm





- 13 Find out the load which can be suspended from a 3.2 mm dia wire taking the factor of safety as 2. Ultimate stress is 25 kg/mm<sup>2</sup>.
- 14 A rod of 60 mm dia is subjected to a maximum tensile load of 1600kg. Calculate the stress and strength of the material if the factor of safety is 5.

## Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.5.10 Heat treatment - Heat treatment and advantages (Only overview required)

#### Heat treatment and its purpose

The properties of steel depend upon its composition and its structure. These properties can be changed to a considerable extent, by changing either its composition or its structure. The structure of steel can be changed by heating it to a particular temperature, and then, allowing it to cool at a definite rate. The process of changing the structure and thus changing the properties of steel, by heating and cooling, is known as 'heat treatment of steel'.

#### Structure of steel when heated (Fig 1)

If steel is heated, a change in its structure commences from 723°C. The new structure formed is called 'Austenite'. Austenite is non-magnetic. If the hot steel is cooled slowly, the old structure is retained and it will have fine grains which makes it easily machinable.



If the hot steel is cooled rapidly the austenite changes into a new structure called 'Martensite'. This structure is very fine grained, very hard and magnetic. It is extremely wearresistant and can cut other metals.

#### Critical temperatures (Fig 2)



#### Lower critical temperature

The temperature, at which the change of structure to austenite starts - 723°C, is called the lower critical temperature for all plain carbon steels.

#### Upper critical temperature

The temperature at which the structure of steel completely changes to AUSTENITE is called the upper critical temperature. This varies depending on the percentage of carbon in the steel. (Fig 2)

#### Example

0.57% and 1.15% carbon steel: In these cases the lower critical temperature is 723°C and the upper critical temperature is 800°C.

For 0.84% carbon steel, both LCT and UCT are 723°C. This steel is called eutectoid steel.

#### Three stages of heat treatment

- Heating
- Soaking
- Quenching

When the steel on being heated reaches the required temperature, it is held in the same temperature for a period of time. This allows the heating to take place throughout the section uniformly. This process is called soaking.

#### Soaking time

This depends upon the cross-section of the steel, its chemical composition, the volume of the charge in the furnace and the arrangement of the charge in the furnace. A good general guide for soaking time in normal conditions is five minutes per 10 mm of thickness for carbon and low alloy steels, and 10 minutes per 10 mm of thickness for high alloy steels.

#### **Heating steel**

This depends on the selection of the furnace, the fuel used for heating, the time interval and the regulation in bringing the part up to the required temperature. The heating rate and the heating time also depend on the composition of the steel, its structure, the shape and size of the part to be heat-treated etc.

#### Preheating

Steel should be preheated at low temperatures up to 600°C as slowly as possible.

#### Quenching

Depending on the severity of the cooling required, different quenching media are used.

The most widely used quenching media are:

- brine solution
- water
- oil
- air

Brine solution gives a faster rate of cooling while air cooling has the slowest rate of cooling.

Brine solution (Sodium chloride) gives severe quenching because it has a higher boiling point than pure water, and the salt content removes the scales formed on the metal surfaces due to heating. This provides a better contact with the quenching medium and the metal being heattreated.

Water is very commonly used for plain carbon steels. While using water as a quenching medium, the work should be agitated. This can increase the rate of cooling.

The quenching oil used should be of a low viscosity. Ordinary lubricating oils should not be used for this purpose. Special quenching oils, which can give rapid and uniform cooling with less fuming and reduced fire risks, are commercially available. Oil is widely used for alloy steels where the cooling rate is slower than plain carbon steels.

Cold air is used for hardening some special alloy steels.

#### Advantages

- To soften the metal.
- To improve toughness.
- To provide better qualities of metal, wear, corrosion and heat resistant metal. Manipulate the microstructure of metal crystallite and refine grain size.
- Relieve stresses set up inside the component during hot or cold working, brazing, casting, forging etc. Homogenize microstructure and remove coring.
- Improve machinability of metal.
- Increase hardness and tensile strength of the metal.
- To improve the electrical and magnetic properties of the metal.
- To reduce the rusting properties.

### Workshop Calculation & Science - TDM (Dies & Moulds) Exercise 2.5.11

# Heat treatment - Different heat treatment process – Hardening, tempering, annealing, normalising, casehardening (Only overview required)

#### Heat treatment processes and purpose

Because steel undergoes changes in structure on heating and cooling, its properties may be greatly altered by suitable heat treatment.

The following are the various heat treatments and their purposes.

Hardening:	To add cutting ability.		
	To increase wear resistance.		
Tempering:	To remove extreme brittleness caused by hardening to an extent.		
	To induce toughness and shock resistance.		
Annealing:	To relieve strain and stress.		
	To eliminate strain/hardness. To improve machinability.		

To soften the steel.

Normalising: To refine the grain structure of the steel.

#### Annealing and normalising

The treatments that produce equilibrium conditions are annealing and normalising.

The treatments that produce non-equilibrium conditions are hardening and tempering (usually done in conjunction with each other).

#### Annealing

In this process, steel is heated to a suitable temperature depending upon its carbon content (Fig 1), and is held at that temperature for sufficient time, and then slowly cooled to room temperature.



The heating, soaking (holding at that temperature) and slow cooling cause the grains to become large, and in the process, produce softness and ductility. For annealing, the hypoeutectoid steel is heated to 30°C to 50°C above the upper critical temperature, and it is 50°C above the lower critical temperature for hypereutectoid steel. (Fig 1)

The soaking time at this temperature is 5 mts/10 mm of thickness for carbon steel.

The cooling rate for carbon steel is 100°C to 150°C/hour.

The cooling is done in the furnace itself by switching off the furnace or the steel iscovered either in sand or dry lime and dry ash.

#### Purpose of annealing

Annealing is done:

- to obtain softness
- · to improve machinability
- · to increase ductility
- to relieve internal stresses
- to reduce or eliminate structural in homogeneity
- to refine grain size and to prepare the steel for subsequent heat treatment processes.

J	•
Carbon content %	Temperature °C
<0.12	875 to 925
0.12 to 0.25	840 to 970
0.25 to 0.50	815 to 840
0.50 to 0.90	780 to 810
0.90 to 1.3	760 to 780

#### Annealing temperature

#### Normalising

Due to continuous hammering or uneven cooling, strains and stresses are formed in the internal structure of steel. These should be removed from forgings or castings; as otherwise, they may fail at any time while in use.

Normalising is done to produce a fine grain for uniformity of the structure and for improved mechanical properties.

#### The normalising process

In this process, the steel is heated to a suitable temperature depending upon its carbon content, (Fig 2) and held at that temperature, and then, cooled freely in the air.

Normalising is usually done, before machining and before hardening, to put the steel in the best condition for these operations.

The steel is heated to a temperature (30 to 40°C above the upper critical temperature) at which only austenite is present even in the case of high carbon steel. This is because this process is the first step towards producing the final properties, and it is necessary to start with austenite to ensure uniformity.



be kept at any wet place, in wet air or kept in forced air as they will induce some hardness.

#### Hardening & tempering

If a piece of steel is heated to a sufficiently high temperature, all the carbon will be dissolved in the solid iron to form a solid solution, called austenite of the steel. When it is slowly cooled, the change in the arrangement of the iron atoms will cause a solid solution called ferrite to be produced. The solid solution can only contain up to 0.006% carbon, and so the excess carbon will be forced to leave the solid solution, and produce cementite. This will, with ferrite, form a laminated structure called pearlite.

#### The principle of hardening

If steel is cooled rapidly (quenched) the excess carbon will not have sufficient time to leave the solid solution with the result that it will be trapped in the iron, and so cause an internal distortion. This internal distortion is the cause for the increase in the hardness of steel with a corresponding reduction in its strength and ductility. This is the basis of the hardening process.

The mechanical properties produced as a result of this treatment will depend upon:

- the carbon content of the steel
- the temperature to which it is heated
- · the duration of heating
- the temperature of the steel at the start of quenching
- the cooling rate produced by quenching.

The effect of carbon content upon the hardness produced by the hardening process is illustrated in Fig 3.



The increase in carbon content will result in an increase in the hardness produced by the treatment.

Steel with less than about 0.15% carbon will not respond to this treatment.

#### **Process of hardening**

In order to produce the desired effect, sufficient carbon must be put into the solid solution to cause internal distortion when it is trapped in the iron by quenching.

When the carbon content is less than 0.83%, the steel is heated to only just above its upper critical point (heating).

When its carbon content is more than 0.83% the steel is heated only to just above its lower critical point (heating).

Fig 4 illustrates the temperatures to which steels are heated before quenching, and the quenching temperature of steels with different carbon content.



#### Soaking time

After heating, the steel is held at that temperature for some time. Normally 5 mts are allowed as soaking time for 10mm thickness of steel.

#### Cooling

Then the steel is cooled in a suitable quenching medium at a certain minimum rate called the critical cooling rate. The critical cooling rate depends upon the composition of the steel. This cooling transforms all the austenite into a fine, needle-like structure called martensite, (the appearance of which is shown in (Fig 5).

The structure of steel treated this way is very hard and strong, but very brittle.

#### The quenching medium

The quenching medium controls the rate of cooling.

For a rapid quenching a solution of salt or caustic soda in water is used.

For very slow quenching a blast of air is sufficient.

Oil gives an intermediate quenching.

Water and oil are the most common quenching media used.

Air quenching is suitable only for certain special alloy steels.



#### Tempering

After hardening, steel is usually reheated to a suitable temperature below the lower critical point (heating) to improve its toughness and ductility but it is done at the expense of hardness and strength. It is done in order to make the steel more suitable for service requirements.

#### Purpose of tempering the steel

Steel, in its hardened condition, is generally too brittle and too severely strained. In this condition, steel cannot be used, and hence it has to be tempered.

The aims of tempering are:

- to relieve the steel from the internal stresses and strains
- to regulate the hardness and toughness
- · to reduce the brittleness
- to restore some ductility.

#### **Process of tempering**

The tempering temperature depends upon the properties required, but it is between 180°C and 650°C. (Fig 6) The duration of heating depends upon the thickness of the material. Tools are usually tempered at a low temperature. The temperature itself is judged by the colour of the oxide film produced on the surface during heating. (Table 1)



This method is not, however, suitable for accurate temperature assessment.

In a manufacturing plant, when heat treating is done on a production basis, modern methods are used. Tempering is done in controlled-atmosphere furnaces with the temperatures controlled by modern instruments. Under such conditions, it is possible to obtain accurate and uniform results in any number of pieces.

#### Table 1

**Tempering temperature** 

Temper colour	Temperature in °C
Pale straw	230
Dark straw	240
Brown	250
Brownish purple	260
Purple	270
Dark purple	280
Blue	300

Fig 7 illustrates the appearance of the microstructure of hardened and then tempered steel.



Generally, tempering in the lower temperature range for an increased time provides greater control in securing the desirable mechanical properties. Such heat treatment may not be feasible under all conditions. For precision work, where results justify the method, and for certain combination of mechanical properties, tempering for long periods of time in a lower temperature range provides a reliable method of getting the desired results.

Fig 8 illustrates how the mechanical properties of hardened steel can be modified by tempering.

#### **Surface Hardening of Steels**

Most of the components must have a hard, wear-resisting surface supported by a tough, shock-resisting core for better service condition and longer life. This combination of different properties can be obtained in a single piece of steel by surface hardening. (Fig 9)

#### Types of surface hardening

- Case hardening
- Nitriding
- Flame hardening
- Induction hardening



#### **Case hardening**

Parts to be hardened by this process are made from a steel with a carbon content of 0.15% so that they will not respond to direct hardening.

The steel is subjected to treatment in which the carbon content of the surface layer is increased to about 0.9%.

When the carburised steel is heated and quenched, only the surface layer will respond, and the core will remain soft and tough as required. (Fig 10)

The surface which must remain soft can be insulated against carburising by coating it with suitable paste or by plating it with copper.

Case hardening takes place in two stages.

- Carburising in which the carbon content of the surface is increased.
- Heat treatment in which the core is refined and the surface hardened.

#### Carburising

In this operation, the steel is heated to a suitable temperature in a carbonaceous atmosphere, and kept at that temperature until the carbon has penetrated to the depth required.

The carbon can be supplied as a solid, liquid or gas.

In all cases, the carbonaceous gases coming from these materials penetrate (diffuse) into the surface of the workpiece at a temperature between 880° and 930°C.

#### Pack carburising (Fig 11)

The parts are packed into a suitable metal box in which they are surrounded by the carburising medium.



The lid is fitted to the box and sealed with fireclay and tied with a piece of wire so that no carbon gas can escape and no air can enter the box to cause decarburisation.

The carburising medium can be wood, bone, leather or charcoal, but an energiser, such as barium carbonate, is added to speed up the process.

#### Liquid carburising

Carburising can be done in a heated salt-bath. (Sodium carbonate, sodium cyanide and barium chloride are typical carburising salts.) For a constant time and temperature of carburisation, the depth of the case depends on the cyanide content.

Salt-bath carburising is very rapid, and is not always suitable because it produces an abrupt change in the carbon content from the surface to the core. This produces a tendency for the case to flake.

This is suitable for a thin case, about 0.25 mm deep. Its advantage is that heating is rapid and distortion is minimised.

#### Gas carburising

The work is placed in a gas-tight container which can be heated in a suitable furnace, or the furnace itself may be the container.

The carburising gas is admitted to the container, and the exit gas in vented.

The gas such as methane or propane may be fed directly into the container in which the work is placed.

In a continuous gas carburising furnace, the carburising, quenching and tempering processes are carried out in sequence in the same closed furnace as they progress on a conveyer from one operation to the next.

Fig 12 illustrates the appearance of the structure across its section produced by carburising.



#### Heat treatment

After the carburising has been done, the case will contain about 0.9% carbon, and the core will still contain about 0.15% carbon. There will be a gradual transition of carbon content between the case and the core.

Owing to the prolonged heating, the core will be coarse, and in order to produce a reasonable toughness, it must be refined.

To refine the core, the carburised steel is reheated to about 870°C and held at that temperature long enough to produce a uniformity of structure, and is then cooled rapidly to prevent grain growth during cooling.

The temperature of this heating is much higher than that suitable for the case, and, therefore, an extremely brittle martensite will be produced.

The case and the outer layers of the core must now be refined.

The refining is done by reheating the steel to about 760  $^{\circ}\text{C},$  to suit the case, and quenching it.

#### Tempering

Finally the case is tempered at about 300°C to relieve the quenching stresses.

If the part is not required to resist shock, it is unnecessary to carry out the core refining operation; in these conditions, a coarse martensite at the surface may not cause trouble, and so this part may be quenched directly after carburising.

Fig 13 illustrates the appearance of the structure across its section produced by case hardening.



#### Nitriding

In the nitriding process, the surface is enriched not with carbon, but with nitrogen. There are two systems in common use, gas nitriding and salt bath nitriding.

#### Gas nitriding

The gas nitriding process consists of heating the parts at 500°C in a constant circulation of ammonia gas for up to 100 hours.

During the gas nitriding process the parts are in an externally heated gas-tight box, fitted with inlet and outlet bores for the ammonia gas which supplies the nitrogen. At the completion of the 'soaking' the ammonia is still circulated until the temperature of the steel has fallen to about 150°C, when the box is opened, and the cooling completed in air. Nitriding causes a film to be produced on the surface but this can be removed by light buffing operation.

#### Nitriding in salt-bath

Special nitriding baths are used for salt-bath nitriding. This process is suitable for all alloyed and unalloyed types of steel, annealed or not annealed, and also for cast iron.

#### Process

The completely stress-relieved workpieces are preheated (about 400°C) before being put in the salt-bath (about 520°C-570°C). A layer 0.01 to 0.02 mm thick is formed on the surface which consists of a carbon and nitrogen compound. The duration of nitriding (half an hour to three hours) depends on the cross-section of the workpiece. (It is much shorter than for gas nitriding.) After being taken out of the bath, the workpieces are quenched and washed in water, and dried.

#### Advantages

The parts can be finish-machined before nitriding because no quenching is done after nitriding, and, therefore, they will not suffer from quenching distortion.

In this process the parts are not heated above the critical temperature, and, hence warping or distortion does not occur.

The hardness and wear-resistance are exceptional. There is a slight improvement in corrosion-resistance as well.

Since the alloy steels used are inherently strong when properly heat treated, remarkable combinations of strength and wear-resistance are obtained.

#### Flame hardening

In this type of hardening, the heat is applied to the surface of the workpiece by specially constructed burners. The heat is applied to the surface very rapidly, and the work is quenched immediately by spraying it with water. (Figs14 and 15) The hardening temperature is generally about 50° C higher than that for full hardening.





The workpiece is maintained at the hardening temperature for a very short period only, so that the heat is not conducted to more than the necessary depth into the workpiece.

Steels used for surface hardening by the flame hardening method will have a carbon content of 0.35% to 0.7%.

#### Induction hardening

This is a production method of surface hardening in which the part to be surface-hardened is placed within an induction coil through which a high frequency current is passed. (Fig 16) The depth of penetration by the heating becomes less, as the frequency increases.



The depth of hardening for high frequency current is 0.7 to 1.0mm. The depth of hardening for medium frequency current is 1.5 to 2.0mm. Special steels and unalloyed steels with a carbon content of 0.35 to 0.7% are hardened.

After induction hardening of workpieces, stress-relieving is necessary.

#### Advantages

The following are the advantages of this type of hardening.

- The depth of hardening, distribution in width and the temperature are easily controllable.
- The time required and the distortion due to hardening are very small.
- The surface remains free from scale.
- This type of hardening can easily be incorporated in mass production.

#### Heat treatment of high speed steel

High speed steels get their name from the fact that they may be operated as cutting tools at much higher speeds than is possible with plain carbon tool steels. Since the maximum hardness of high speed steel is obtained on tempering at high temperatures, it can be operated as a cutting tool in the same temperature range without loss of hardness. That is, the rise in temperature due to friction will not reduce the temper of the tool point as it cuts into the steel. Tool steels are often annealed for softening before machining or forming, and also for obtaining grain refinement.

#### Annealing

Soak at 900°C for about four hours. Then cool slowly at not more than 20°C per hour to 600°C. It may then be cooled to room temperature in still air.

#### Hardening

Preheat to 850° C slowly to prevent cracking. Then heat rapidly in a salt-bath furnace approximately to 1250°C depending upon the alloy used. This rapid heating in a salt-bath furnace reduces grain growth and prevents oxidation of steel during heating. Quench in an air blast or oil depending on the mass of the component. When a salt bath furnace is not available, this can be minimised in a double chamber muffle furnace (Fig 17) by using the excess fuel to give a carburising atmosphere. However, this reduces the combustion efficiency, and there may be some difficulty in reaching the hardening temperature. With high temperature salts available, modern practice favours the use of the salt-bath furnace. (Fig 18 and 19)



#### Secondary hardening (Tempering )

This is sometimes called tempering. However, this term is not strictly true. Not only does secondary hardening increase the toughness of the steel, it also increases the hardness whereas tempering increases the toughness at the expense of hardness. The effect of secondary hardening helps these steels to work effectively at higher temperatures than plain carbon tool steels.

#### Heat treatment of non ferrous metals

#### Annealing

Like steel, non-ferrous metals can be softened by heating and allowing to cool. However, since they cannot be hardened by rapid cooling, the rate of cooling is comparatively unimportant. In fact, copper components are often quenched in water. This not only saves time but also cleans the black oxide film from the surface of the components because of the rapid contraction.





#### Hardening

Only a very few non-ferrous alloys can be hardened by heating and quenching like steel and most non-ferrous metals are hardened by cold working. As anyone, who has worked as a coppersmith will know, the metal starts to work-harden as it is beaten to shape and it must be annealed from time to time to prevent it from cracking.

## Assignment A

- 1 a What is two purpose of Hardening.
  - b What is the purpose of normalising.
  - c Write four annealing purposes.
  - d What is the purpose of tempering.
  - e What is the purpose of annealing.
  - f Which cooling process is suitable for annealing.
  - g Which cooling process is suitable for normalising.
  - h What type of structure in the normalising process.
  - i What reason the steel is reheated (after hardening) to a suitable temperature (180°C to 650°C).
  - j Why steel is reheated.
- 2 i What is the heating method for nitriding?
  - a Temperature controlled furnace
  - b Electric induction coil heat
  - c By use of Oxy-Acetylene torches
  - d By Ammonia gas
  - ii What is the heating method for flame hardening?
    - a Temperature controlled furnace
    - b Electric induction coil heat
    - c By use of Oxy-Acetylene torches
    - d By Ammonia gas Hardening Process
  - iii What is the heating method for induction hardening?
    - a Temperature controlled furnace
    - b Electric induction coil heat
    - c By use of Oxy-Acetylene torches
    - d By Ammonia gas

- iv What is the heating method for normal hardening?
  - a Temperature controlled furnace
  - b Electric induction coil heat
  - c By use of Oxy-Acetylene torches
  - d By Ammonia gas
- v Which quenching medium for hardening of H.S Steel?
  - a Water spray
  - b Still air
  - c Bath of water
  - d Air blast or oil
- vi Which quenching medium for hardening of carbon steel?
  - a Water spray
  - b Still air
  - c Bath of water
  - d Air blast or oil
- vii Which quenching medium for normalising low carbon or medium carbon steel?
  - a Water spray
  - b Still air
  - c Bath of water
  - d Air blast or oil
- viii Which quenching medium for flame hardening?
  - a Water spray
  - b Still air
  - c Bath of water
  - d Air blast or oil

### **B MCQ (Multiple Choice Questions)**

- 1 The process of changing the structure of a metal by heating and cooling is
   3 The quenchi

   A Heat treatment
   B Machining
   A normal
  - C Hot rolling D Melting
- 2 The three stages of heat treatment is Heating, Soaking, and
  - A Smelting B Quenching
  - C Hardening D Tempering

- 3 The quenching oil viscosity should be.
  - normal B medium
    - D high

**B** Normalising

- 4 Which relieves stress and strain.
  - A Hardening
  - C Tempering D Annealing

- 5 Which process produce equilibrium conditions.
  - A Annealing and Normalising
  - B Hardening and Tempering
  - C Annealing and Hardening
  - D Normalising and Tempering
- 6 Which quenching medium is commonly used.
  - A Water & Lead B Water & Oil
  - C Water & Brine solution D Lead & Brine solution
- 7 Which process is used to reduce the brittleness.
  - A Annealing B Normalising
  - C Tempering D Case hardening

- 8 What is the purpose of Nitriding process.
  - A partial B whole
  - C case D surface
- 9 Which temperature change structure to austenite.
  - A lower B upper
  - C higher D larger
- 10 Which temperature change structure of steel to austenite
  - A lower B upper
  - C smaller D lesser

# Estimation and Costing - Simple estimation of the requirement of material etc., as applicable to the trade - Hand injection mould assembly

#### Introduction

Estimation is the method of calculating the various quantities and the expenditure to be incurred on a particular job or process.

Estimate is the method used to measure or quantify the different quantities and the expected expenditure to be incurred on a particular work or project.

We know that the estimation is long procedure, and its totally depends upon the projects,

In case the funds available are less than the estimated cost the work is done in part or by reducing it or specifications are altered,

The following essential details are required for preparing an estimate.

Drawings like plan, elevation and sections of important parts.

Detailed specifications about workmanship & properties of materials, etc.

Standard schedule of rates of the current year.

Estimating is the process of preparing an approximation of quantities which is a value used as input data and it is derived from the best information available.

An estimate that turns out to be incorrect will be an overestimate if the estimate exceeded the actual result, and an underestimate if the estimate fell short of the actual result.

A cost estimate contains approximate cost of a product process or operation. The cost estimate has a single total value and it is inclusive of identifiable component values.

#### **Purpose of Estimating and Costing**

- 1 Estimates provide an rough idea of the cost of the job and therefore its feasibility can be calculated, i.e. whether or not the project would be included in the funds available.
- 2 Estimate gives an idea of the time needed to complete the work.
- 3 Estimates are required to invite tenders and quotations and to arrange the contracts.

- 4 Estimates are also required to control expenditure during the execution of the work.
- 5 Estimates decide whether or not proposed plan matches the funds available.

#### **Estimation Methods**

Estimate involves the following operations

- Preparing detailed Estimate.
- Calculating the rate of each unit of work.
- Preparing abstract of estimate.

**Estimation** is the process of calculating or evaluating a quantity by estimation, that is, without reference to specific measurements. Estimating is a fundamental process in all engineering.

This is usually done before purchase or construction begins or during preliminary planning stages. Estimating is usually more accurate, but there are a few limitations namely that if your estimate relies on labour costs, you'll need to know how many man-hours will take to complete the project.

Estimates are developed from observations and knowledge of past experience. The accuracy of an estimate often depends on the level of detail available and the amount of time for which data are available for analysis.

**Costing** is the process of estimating the cost of a project before it's completed. It can be done with an itemized list, or through estimation using a construction cost calculator.

Costing includes three steps: estimating, bidding, and finalizing. It helps predict how much money will be required to construct the project.

A "costing" typically refers to how much it will cost someone to produce a single unit.

#### There are two types of costings

**Independent costing** - this is the cost of direct material and labour costs. This type of costing only takes into account the cost of a single-phase, so it's not representative of the overall project cost.

**Cumulative Costing -** this type of costing looks at the total cost for all phases of work, but it can be difficult to ensure that estimates are accurate.

Exercise: Hand Injection Mould Assembly (Fig 1)









Cavity Plate - Part No.2 (Fig 3)



Cavity plate size	= 90.5 x 90.5 x 10.7 mm
Raw material size	= 95 x 95 x 12 mm
Volume	$= \ell \mathbf{x} \mathbf{b} \mathbf{x} \mathbf{h}$
	= 9.5 x 9.5 x 1.2 cm
Volume	= 108.3 cm <sup>3</sup>
Weight	= Volume x Density
Density	= 7.8 gm/cm <sup>3</sup>
	= 108.3 x 7.8
	= 844.74 grams



Raw material cost = Rs.100/Kg

Material cost = 0.845 Kg x Rs.100

= Rs.84.50

=Rs.85

#### Core Retainer - Part No.3 (Fig 4)



Core retainer size =  $90.5 \times 90.5 \times 25.5 \text{ mm}$ Raw material size =  $95 \times 95 \times 28 \text{ mm}$ =  $9.5 \times 9.5 \times 2.8 \text{ cm}$ Volume =  $\ell \times b \times h$ =  $9.5 \times 9.5 \times 2.8 \text{ cm}$ Volume =  $252.7 \text{ cm}^3$ Weight = Volume x Density Density =  $7.8 \text{ gm/cm}^3$ =  $252.7 \times 7.8$ = 1971 grams= 1.97 KgRaw material cost = Rs.100/KgMaterial cost =  $1.97 \text{ Kg} \times \text{Rs.100}$ = Rs.197

#### Bottom Plate - Part No.4 (Fig 5)



#### Top plate - Part No.5 (Fig 6)





#### Insert Holder - Part No.6 (Fig 7)



Weight = Volume x Density  
Density = 
$$7.8 \text{ gm/cm}^3$$
  
=  $6.75 \times 7.8$   
=  $52.65 \text{ grams}$   
=  $0.0526 \text{ Kg}$   
Raw material cost =  $\text{Rs.100/Kg}$   
Material cost =  $0.0526 \text{ Kg} \times \text{Rs.100}$   
=  $\text{Rs.5.26}$ 

#### Insert - Part No.7 (Fig 8)



Insert size	= Ø16 x 15 mm
	= Ø1.6 x 1.5 cm
Volume	= $\pi r^2 h$
d	= 1.6 cm
r	= 0.8 cm
	= 3.14 x 0.8 x 0.8 x 1.5 cm <sup>3</sup>
	= 3.14 x 6.4 x 1.5
	= 3.014 cm <sup>3</sup>
Weight	= Volume x Density
Density	= 7.8 gm/cm <sup>3</sup>
	= 3.014 x 7.8
	= 23.512 grams
	= 0.0235 Kg
Raw material cost	= Rs.100/Kg
Material cost	= 0.0.235 x Rs.100
	=Rs.2.35

#### Dovel pin - Part No.8 (Fig 9)



Dovel pin size =  $\emptyset 5 \times 25$  mm Raw material size =  $\emptyset 0.5 \times 2.5$  cm

Volume =  $\pi r^2 h$ 

- d = 0.5 cm
- r = 0.25 cm

= 3.14 x 0.25 x 0.25 x 2.5 cm<sup>3</sup> = 0.49 cm<sup>3</sup> Weight = Volume x Density Density =  $7.8 \text{ gm/cm}^3$ = 0.49 x 7.8 = 3.82 grams = 0.0038 Kg Raw material cost = Rs.100/Kg Material cost = 0.0038 x Rs.100 =Rs.0.38 Total Material cost for Part Nos.5, 10, 11, 12, 13, 14 and 15 = Rs.17 + Rs.85 + Rs.197 + Rs.310 + Rs.5.62 + Rs.2.40 + Rs.0.38

= Rs.617.40

## Estimation and Costing - Simple estimation of the requirement of material etc., as applicable to the trade - Two cavity injection mould parts

#### Exercise

#### Guide pillar (4 Nos.) (Fig 1)



#### Guide Bush (4 Nos.) (Fig 2)



#### Ejector Sprue Bush (1 No.) (Fig 3)



#### Register Ring (1 No.) (Fig 4)



5 5	
Raw material size	= Ø120 x 15 mm
Volume	= $\pi$ r <sup>2</sup> h
d	= 120 cm
r	= 60 cm
	= 3.14 x 60 x 60 x 15 mm
	= 3.14 x 6 x 6 x 1.5 cm <sup>3</sup>
	= 169.56 cm <sup>3</sup>
Weight	= Volume x Density
Density	= 7.8 gm/cm <sup>3</sup>
	= 169.56 x 7.8
	= 1322.56 grams
	= 1.323 Kg
Raw material cost	= Rs.100/Kg
Material cost	= 1.323 x Rs.100
	=Rs.132.25

# Estimation and Costing - Problems on estimation and costing - Hand injection mould assembly

#### Guide pin (2 Nos.) - Part No.1 (Fig 1)



- 1 Hold the job in a 3 jaw chuck
- 2 Face one side first and turn the outer diameter to  $\emptyset$ 14.5 x 27mm length and step turn  $\emptyset$ 18.5 x 5 mm length
- 3 Make 2 Guide pins

Calculation:

Total cost	=	Rs.417.14
Raw material cost for 2 pins		Rs.17.14
Lathe charge	=	Rs.400/hour
Total hours require for 2 pins		1 hour
# Cavity plate - Part No.2 (Fig 2)



	Total	840 mins
6	Make cavity plate as per component	480 mins
5	Make hole and thread for M5 and M8	30 mins
4	Make drill hole for guide pin $\varnothing$ 14 mm and dowel hole $\varnothing$ 5 mm	60 mins
3	Punch witness marks as per marking in the cavity plate	30 mins
2	Apply marking media and mark as per job drawing of cavity plate	120 mins
1	File and finish to size 90 x 90 x 10.15 mm maintaining parallel and perpendicularity	120 mins

	Total time	=	840 mins
Total com	plition of cavity plate	=	$\frac{840}{60}$ = 14 hours
Labour charge for making cavity plate		=	Rs.200/hour
Cavity plate making charge		=	14 hours x Rs.100
		=	Rs.2800
Total cost			
1	Material cost	=	Rs. 84.50
2	Labour charge	=	Rs.2800.00

Total cost	=	Rs.2884.50
Labourcharge	=	Rs.2800.00

# Core retainer plate - Part No.3 (Fig 3)



		Total	420 mins
4	Make centre for core fixing of square 10 H7 and $\varnothing$ 22.33 mm as per drawing		120 mins
3	Guide pin hole & counter shank and tap thread M8		120 mins
2	Apply marking media and mark as per core retainer drawing such as dowel holes		60 mins
1	File and finish to size 90 x 90 x 25 mm		120 mins

Total Time	=	420 minutes
Total hours	=	$\frac{420}{60} = 7 \text{ hours}$
Labour charge	=	Rs.200/hour
	=	Rs.200 x 7 hours
	=	Rs.1400
Total cost		

	Total cost	=	Rs.1597.00
2	Labourcharge	=	Rs.1400.00
1	Material cost	=	Rs. 197.00



		Total	180 mins
4	Make dowel hole 5 mm and free hole & counter shank hole for M8 screw		30 mins
3	Mark and make component part of R 20.3 mm on the centre portion		60 mins
2	Apply marking media and make as per bottom plate drawing		30 mins
1	File and finish to size 90 x 90 x 20 mm		60 mins

Total

# **Calculation:**

Total time	=	180 minutes
Total hours	=	$\frac{180}{60} = 3 \text{ hours}$
Labour charge	=	Rs.100/hour
	=	3 hours x Rs.100
	=	Rs.300

	Total cost	=	Rs. 454.90
2	Labour charge	=	Rs.300.00
1	Material cost	=	Rs.154.90

# Top plate - Part No.5 (Fig 5)



		Total	120 mins
3	Make drill hole and counter shank hole for M8 & M5		30 mins
2	Apply marking media and mark as per top plate drawing		30 mins
1	File and finish to size 90 x 90 x 20 mm		60 mins

# Calculation:

Total time	=	120 minutes
Total hours	=	$\frac{120}{60} = 2 \text{ hours}$
Labourcharge	=	Rs.100/hour
	=	2 hours x 100
	=	Rs.200

	Total cost	=	Rs. 354.90
2	Labour charge	=	Rs.200.00
1	Material cost	=	Rs. 154.90



- 1 Hold the job in a 3 jaw chuck
- 2 Turn Ø8 mm x 7 mm length
- 3 File and make as square 10 mm x 14.85 mm length
- 4 Make thread M8 x 7 mm length and centre of sqaure make internal thread M8 x 10 mm length

## **Calculation:**

Total cost		
	=	Rs.200
	=	Rs.200 x 1 hour
Machining charge to make Insert holder	=	Rs.200/hour
Total time	=	1 hour

1Material cost=Rs. 5.262Machining charge to

make Insert holder = Rs. 200.00

Total cost = Rs. 205.26

#### Insert - Part No.7 (Fig 7)



- 1 Hold the job in a 3 jaw chuck
- 2 Face and turn Ø16 x 15 mm length
- 3 Make thread M8 x 12 mm length by tap

Total cost	=	Rs. 202.40
2 Machining charge	=	Rs.200.00
1 Material cost	=	Rs. 2.40
Total cost		
	=	Rs.200
	=	Rs.200 x 1 hour
Machining charge to make Insert	=	Rs.200/hour
Total time	=	1 hour

# Dowel pin (2 Nos.) - Part No.8 (Fig 8)



1 Hold the job in 3 jaw chuck.

2 Face and turn Ø5x 25 mm length

## **Calculation:**

Total time	= 1 hour
Labour charge	= Rs.200/hour
	= Rs.200 x 1 hour
	= Rs.200

# **Total cost**

1	Material cost	=	Rs.	0.38
2	Labour charge	=	Rs.2	200.00

Total cost = Rs. 200.38

#### Total cost of Hand injection mould

Total cost =			Rs. 6317.38
8	Dowel pin	=	Rs. 200.38
7	Insert	=	Rs. 202.40
6	Insertholder	=	Rs. 205.26
5	Topplate	=	Rs. 354.90
4	Bottom plate	=	Rs. 454.90
3	Core retainer plate	=	Rs. 1597.90
2	Cavity plate	=	Rs. 2884.50
1	Guide pin	=	Rs. 417.14

# Hand Injection Mould Assembly (Fig 9)



		Total	180 mins
8	Clamp the insert to the insert holder.		20 mins
7	Clamp the insert holder to the top plate with SHCS M5 x 20mm depth.		20 mins
6	Clamp the top plate to core retainer with SHCS M8 x 25mm depth (2 Nos)		20 mins
5	Fit the insert holder to the core retainer.		20 mins
4	Fit the guide pin into the core retainer.		20 mins
3	Clamp the cavity plate to the bottom plate with SHCS M8 x 20mm depth (2 Nos.	)	20 mins
2	Keep the cavity plate on the bottom plate and drive dowels dia 5 x 20mm depth ( into the reamed holes.	2 Nos)	30 mins
1	Fix the cavity plate on the bottom plate with SHCS M8 x 20mm depth (2Nos) su the references of both the plates are in one line.	ch that	30 mins

Assembly charge	=	Rs.300
	=	Rs.100 x 3 hours
Assembly labour charge	=	Rs.100/hour
	=	3 Hours
Total Assembly time	=	180 minutes

Exercise 2.6.15

# Estimation and Costing - Problems on estimation and costing - Two cavity injection mould parts

# Guide Pillar - 4 Nos. (Fig 1) - Operation in CNC machine



- 1 Check the raw material size
- 2 Study the part drawing and list out the tools required.
- 3 Prepare the part programme for turning.
- 4 Verify the part programme using simulator.
- 5 Enter the part programme in CNC machine operator console.
- 6 Set the workpiece in CNC turning centre.
- 7 Get it checked by the trainer.
- 8 Set the tool in turret in position as per programme.
- 9 Measure the work offset and enter in G54.
- 10 Measure the tool offset for all the tools and enter in the tool geometry page, tool nose radius and style of tool.
- 11 Check the work and tool offsets.
- 12 If there is any mistake correct it or ask the trainer for guidance.
- 13 Run the programme in single block by dry run or setting the offset away from work zero.
- 14 If any corrections, correct it accordingly and run the programme.
- 15 Check all the dimensions.
- 16 Remove the workpiece from the machine.
- 17 Switch off the machine.

# **Calculation:**

Total time = 1 hour

For 4 Nos. =  $4 \times 1$  hour = 4 hours

- CNC charge = Rs.400/hour
  - = Rs.400 x 4
  - = Rs.1600

# Total cost

- 1 Material cost = Rs. 220.56
- 2 CNC charge for Guide pillar = Rs.1600.00

Total cost = Rs.1820.56

#### Guide Bush - 4 Nos. (Fig 2) - Operation in CNC machine



- 1 Check the raw material size
- 2 Study the part drawing and list out the tools required.
- 3 Prepare the part programme for turning.
- 4 Verify the part programme using simulator.
- 5 Enter the part programme in CNC machine operator console.
- 6 Set the workpiece in CNC turning centre.
- 7 Get it checked by the trainer.
- 8 Set the tool in turret in position as per programme.
- 9 Measure the work offset and enter in G54.
- 10 Measure the tool offset for all the tools and enter in the tool geometry page, tool nose radius and style of tool.
- 11 Check the work and tool offsets.
- 12 If there is any mistake correct it or ask the trainer for guidance.
- 13 Run the programme in single block by dry run or setting the offset away from work zero.
- 14 If any corrections, correct it accordingly and run the programme.
- 15 Check all the dimensions.
- 16 Remove the workpiece from the machine.
- 17 Switch off the machine.

#### Calculation:

Total time	=	1 hour
For 4 Nos.	=	$4 \times 1$ hour = 4 hours
CNC charge	=	Rs.400/hour
	=	Rs.400 x 4 hours
	=	Rs.1600

	Total cost	=	Rs. 1	688
2	CNC charge for Guide bush	=	Rs.1	600
1	Material cost	=	Rs.	88

#### Ejector Sprue Bush (Fig 3) - Operation in CNC machine



- 1 Check the raw material size
- 2 Study the part drawing and list out the tools required.
- 3 Prepare the part programme for turning.
- 4 Verify the part programme using simulator.
- 5 Enter the part programme in CNC machine operator console.
- 6 Set the workpiece in CNC turning centre.
- 7 Get it checked by the trainer.
- 8 Set the tool in turret in position as per programme.
- 9 Measure the work offset and enter in G54.
- 10 Measure the tool offset for all the tools and enter in the tool geometry page, tool nose radius and style of tool.
- 11 Check the work and tool offsets.
- 12 If there is any mistake correct it or ask the trainer for guidance.
- 13 Run the programme in single block by dry run or setting the offset away from work zero.
- 14 If any corrections, correct it accordingly and run the programme.
- 15 Check all the dimensions.
- 16 Remove the workpiece from the machine.
- 17 Switch off the machine.

#### **Calculation:**

Total time	=	3 hour
CNC charge	=	Rs.400/hour
	=	Rs.400 x 3 hours
	=	Rs.1200

		-	
	Total cost	= Rs. '	1249.00
2	CNC charge for Ejector sprue bush	= Rs.	1200.00
1	Material cost	= Rs.	49.00

## Register Ring (Fig 4) - Operation in CNC machine



- 1 Check the raw material size
- 2 Study the part drawing and list out the tools required.
- 3 Prepare the part programme for turning.
- 4 Verify the part programme using simulator.
- 5 Enter the part programme in CNC machine operator console.
- 6 Set the workpiece in CNC turning centre.
- 7 Get it checked by the trainer.
- 8 Set the tool in turret in position as per programme.
- 9 Measure the work offset and enter in G54.
- 10 Measure the tool offset for all the tools and enter in the tool geometry page, tool nose radius and style of tool.
- 11 Check the work and tool offsets.
- 12 If there is any mistake correct it or ask the trainer for guidance.
- 13 Run the programme in single block by dry run or setting the offset away from work zero.
- 14 If any corrections, correct it accordingly and run the programme.
- 15 Check all the dimensions.
- 16 Remove the workpiece from the machine.
- 17 Switch off the machine.

# Calculation:

Total time	=	5 hour
CNC charge	=	Rs.400/hour
	=	Rs.400 x 5 hours
	=	Rs.2000

# **Total cost**

- 1 Material cost = Rs. 132.25
- 2 CNC charge for Register ring = Rs.2000.00
  - Total cost = Rs.2132.25

# **Cost of Injection Mould parts**

	Total cost =		Rs. 6889.81
4	Registerring	=	Rs. 2132.25
3	Ejector sprue bush	=	Rs. 1249.00
2	Guide bush	=	Rs. 1688.00
1	Guide pillar	=	Rs. 1820.56